



Chemical Compatibility Guide for: Ammex Gloves

NOTICE:

The guide on the following page(s) was provided by the supplier. New Pig Corporation assumes no responsibility, obligation, or liability in conjunction with the use or misuse of the information.

**For additional assistance, please contact New Pig Technical Services at
1-800-HOT-HOGS® (468-4647).**

100% Money-Back Guarantee

If you're not happy with a product, for any reason, we'll refund every penny of your purchase price. That means we'll refund all sales taxes, shipping costs, and any other incidentals - without tacking on a restocking fee or any other surprise charges. You get ALL your money back. Period.

One Pork Avenue, Tipton, PA 16684-0304 • 1-800-HOT HOGS® (468-4647) • Fax: 1-800-621-PIGS (7447)
Email: hothogs@newpig.com • Web: newpig.com

© New Pig Corporation. All rights reserved.

This chemical resistance chart is for advisory use only.

Conditions, exposure times, chemical concentrations and residues may effect

glove performance. It is strongly advised that on-site testing of all gloves is important to determining safe usage

Chemical Resistance	Nitrile	Latex	Vinyl
Acetaldehyde	Recommended	Recommended	Recommended
Acetic Acid	Recommended	Recommended	Recommended
Acetone	Limited Use	Recommended	Limited Use
Acetonitrile	Not Rated	Limited Use	Not Rated
Ammonium Fluoride (40%)	Recommended	Recommended	Recommended
Ammonium Hydroxide (30%)	Recommended	Recommended	Recommended
Amyl Acetate	Recommended	Limited Use	Not Recommended
Amyl Alcohol	Recommended	Recommended	Not Rated
Aniline	Recommended	Recommended	Limited Use
Animal Fats	Recommended	Not Recommended	Recommended
Aqua Regia	Not Rated	Not Rated	Recommended
Battery Acid	Recommended	Recommended	Recommended
Benzaldehyde	Recommended	Limited Use	Recommended
Benzene	Recommended	Not Recommended	Limited Use
Benzyl Chloride	Recommended	Limited Use	Not Recommended
Bromopropionic Acid	Not Rated	Recommended	Not Rated
Butane	Recommended	Not Recommended	Not Recommended
2-Butoxyethanol	Recommended	Not Rated	Not Rated
Butyl Acetate	Limited Use	Not Recommended	Not Rated
Butyl Alcohol	Recommended	Recommended	Recommended
Butyl Cellosolve	Recommended	Recommended	Not Rated
γ -Butyrolactone	Not Rated	Recommended	Not Rated
Calcium Hypochlorite	Recommended	Not Recommended	Recommended
Carbolic Acid	Not Recommended	Not Recommended	Recommended
Carbon Dichloride	Recommended	Not Rated	Not Rated
Carbon Disulfide	Recommended	Not Recommended	Not Recommended
Carbon Tetrachloride	Recommended	Not Recommended	Limited Use
Castor Oil	Recommended	Recommended	Recommended
Cellosolve Acetate	Recommended	Recommended	Not Rated
Cellosolve Solvent	Recommended	Recommended	Not Rated
Chloroform	Recommended	Not Recommended	Not Recommended
Chloronaphalenes	Limited Use	Not Rated	Not Rated
Chlorothene VG	Limited Use	Not Rated	Not Recommended
Chromic Acid (50%)	Recommended	Not Recommended	Recommended
Citric Acid (10%)	Recommended	Recommended	Recommended
Cottonseed Oil	Recommended	Not Recommended	Recommended
Creosol	Recommended	Not Recommended	Limited Use
Cunene	Recommended	Not Rated	Not Rated
Cutting Oil	Recommended	Limited Use	Not Recommended
Cyclohexane	Recommended	Not Recommended	Not Recommended
Cyclohexanol	Recommended	Not Recommended	Recommended
Dibutyl Phthalate	Recommended	Limited Use	Recommended
Diamine	Recommended	Not Rated	Not Rated

Diethylamine	Limited Use	Not Rated	Not Rated
Diethyl Ether	Recommended	Limited Use	Not Recommended
Di-Isobutyl Ketone (DIBK)	Recommended	Not Recommended	Not Recommended
Dimethyl Acetamide (DMAC)	Not Rated	Limited Use	Not Rated
Dimethyl Formamide (DMF)	Not Rated	Recommended	Not Rated
Dimethyl Sulfoxide (DMSO)	Recommended	Recommended	Not Rated
Diocetyl Phthalate (DOP)	Recommended	Not Recommended	Not Rated
Dioxane	Not Rated	Limited Use	Not Rated
Ethanol	Recommended	Not Rated	Not Rated
2-Ethoxyethanol	Recommended	Not Rated	Not Rated
Ethyl Acetate	Recommended	Limited Use	Limited Use
Ethyl Alcohol	Recommended	Recommended	Recommended
Ethylene Dichloride	Recommended	Not Recommended	Not Recommended
Ethylene Glycol	Recommended	Recommended	Recommended
Ethyl Glycol Ether	Recommended	Not Rated	Not Rated
Ethylene Trichloride	Not Recommended	Not Recommended	Not Rated
Formaldehyde (37%)	Recommended	Recommended	Recommended
Formalin Solution	Recommended	Not Rated	Not Rated
Formic Acid	Recommended	Recommended	Recommended
Freon TF	Recommended	Not Rated	Not Rated
Furfural	Not Rated	Recommended	Not Rated
Gasoline	Recommended	Not Rated	Not Recommended
Glycerine	Recommended	Recommended	Recommended
Glycerol	Recommended	Recommended	Recommended
Heptane	Recommended	Not Rated	Not Rated
Hexamethyldisilazane	Recommended	Not Rated	Not Rated
Hexane	Recommended	Not Rated	Not Rated
Hydraulic Fluid-Petrol Based	Recommended	Not Recommended	Recommended
Hydraulic Fluid- Ester Based	Not Recommended	Not Recommended	Not Recommended
Hydrazine 65%	Recommended	Recommended	Recommended
Hydrochloric Acid (Conc.)	Recommended	Recommended	Recommended
Hydrofluoric Acid (48%)	Recommended	Recommended	Recommended
Hydrogen Peroxide (30%)	Recommended	Recommended	Recommended
Hydroquinone	Recommended	Recommended	Recommended
Isobutyl Alcohol	Recommended	Recommended	Limited Use
Iso-Octane	Recommended	Not Rated	Not Recommended
Isopropanol	Recommended	Not Rated	Not Rated
Isopropyl Alcohol	Recommended	Recommended	Recommended
Isopropyl Benzene	Recommended	Not Rated	Not Rated
Kerosene	Recommended	Not Recommended	Limited Use
Lactic Acid (85%)	Recommended	Recommended	Recommended
Lauric Acid (36%)	Recommended	Recommended	Limited Use
Linoleic Acid	Recommended	Not Recommended	Recommended
Linseed Oil	Recommended	Not Recommended	Recommended
Maleic Acid	Recommended	Recommended	Recommended
Methanol	Recommended	Not Rated	Not Rated
Methyl Acetate	Not Recommended	Not Recommended	Not Rated
Methyl Alcohol	Recommended	Recommended	Recommended
Methylamine	Recommended	Recommended	Recommended
Methyl Cellosolve	Limited Use	Not Recommended	Not Rated
Methylamine	Recommended	Recommended	Recommended

Methyl Ethyl Ketone (MEK)	Limited Use	Recommended	Not Recommended
Methyl Isobutyl Ketone	Not Recommended	Limited Use	Not Rated
Methyl Methacrylate	Not Recommended	Not Recommended	Not Rated
Methyl-T-Butyl Ether	Recommended	Not Rated	Not Rated
Mineral Oil	Recommended	Not Recommended	Limited Use
Mineral Spirits	Recommended	Not Rated	Limited Use
Monoethanolamine	Recommended	Recommended	Recommended
Morpholine	Not Rated	Recommended	Not Rated
Muriatic Acid (37.5%)	Recommended	Recommended	Recommended
N-Methyl-2 Pyrrolidone	Not Rated	Recommended	Not Rated
Naphthalene	Recommended	Recommended	Recommended
Naptha VM&P	Recommended	Not Rated	Not Recommended
Nitric Acid (70%)	Not Recommended	Limited Use	Recommended
Nitrobenzene	Not Rated	Not Recommended	Not Rated
Nitromethane	Limited Use	Recommended	Not Recommended
Nitropropane	Not Rated	Recommended	Not Rated
Octyl Alcohol	Recommended	Recommended	Limited Use
Oleic Acid	Recommended	Not Recommended	Limited Use
Oxalic Acid	Recommended	Recommended	Recommended
Paint Remover	Recommended	Limited Use	Not Recommended
Palmitic Acid	Recommended	Recommended	Recommended
Pentachlorophenol	Recommended	Not Recommended	Limited Use
Pentane	Recommended	Not Recommended	Not Rated
Pentachlorophenol	Recommended	Not Rated	Not Rated
Perchloric Acid (60%)	Recommended	Not Recommended	Recommended
Perchloroethylene	Recommended	Not Rated	Not Rated
Perholfteum Ether	Recommended	Not Rated	Not Rated
Phenol	Not Rated	Recommended	Recommended
Phosphoric Acid (85%)	Recommended	Recommended	Recommended
Picric Acid	Recommended	Recommended	Recommended
Potassium Hydroxide (sat.)	Recommended	Recommended	Recommended
Printing Ink	Recommended	Recommended	Limited Use
Propyl Acetate	Limited Use	Not Recommended	Not Rated
Propyl Alcohol	Recommended	Recommended	Limited Use
Propylene Oxide	Not Rated	Not Recommended	Not Rated
Rubber Solvent	Recommended	Not Rated	Not Rated
Rule Solvent	Recommended	Not Rated	Not Rated
Sodium Hydroxide (50%)	Recommended	Recommended	Recommended
Sodium Hypochlorite	Limited Use	Recommended	Recommended
Stoddard Solvent	Recommended	Not Recommended	Not Rated
Sulfuric Acid (50%)	Recommended	Recommended	Recommended
Tannic Acid (65%)	Recommended	Recommended	Recommended
Toluene	Recommended	Not Recommended	Limited Use
Toluene Di-Isocyanate (TDI)	Not Rated	Not Recommended	Not Recommended
Trichlorethylene (TCE)	Recommended	Not Rated	Not Rated
Trichlorotrifluoroethane	Recommended	Not Rated	Not Rated
Tricresyl Phosphate (TCP)	Recommended	Recommended	Limited Use
Triethanolamine (85%) (TEA)	Recommended	Recommended	Recommended
Tung Oil	Recommended	Not Rated	Limited Use
Turbine Oil	Recommended	Not Recommended	Limited Use
Turpentine	Recommended	Not Recommended	Not Recommended

Vegetable Oil	Recommended	Not Recommended	Limited Use
Xylene	Recommended	Not Rated	Not Rated