

Chemical Compatibility Guide for: SHOWA 707HVO Biodegradable Nitrile Gloves

The guide on the following page(s) was provided by the supplier. New Pig Corporation assumes no responsibility, obligation, or liability in conjunction with the use or misuse of the information.



New Pig

One Pork Avenue
Tipton, PA 16684-0304

newpig.com

North America: **1-800-468-4647**

Europe: **+31 (0)76 596 92 50**

China: **+86-21-400 921 5178**

PIG, PIG logo are registered trademarks in USA and other countries. See tm.newpig.com


UK: **0800 919 900**

Outside North America: **+1-814-684-0101**



707HVO

Material Nitrile LENGTH 12 in. / 305mm



CHEMICAL PERMEATION

CHEMICAL NAME	CAS NUMBER	BDT	
		TTL ASTM F739	INT ASTM F1383
Formaldehyde 37%	50-00-0	NT	>240
2-Hydroxypropionic acid 85%	50-21-5	NT	>240
Carbon Tet	56-23-5	NT	>240
Urea (s) 99%	57-13-6	>480	>240
1,2-Propanediol	57-55-6	>480	>240
Diethyl Ether	60-29-7	1-5	1-5
Aminobenzene	62-53-3	NT	>10
Ethanol	64-17-5	>60	>120
Formic Acid 90%	64-18-6	>10	NT
Acetic Acid 5%	64-19-7	>480	>240
Acetic Acid 10%	64-19-7	>480	>240
Acetic Acid 84%	64-19-7	NT	>60
Acetic Acid 50%	64-19-7	>480	>240
Acetic Acid 25%	64-19-7	>480	>240
Acetic Acid 99%	64-19-7	NT	>60
Benzoic Acid (s) 99%	65-85-0	>480	>240
Methanol	67-56-1	NT	>60
2-Propanol	67-63-0	>480	>240
2-Propanone	67-64-1	1-5	1-5
Chloroform	67-66-3	1-5	1-5
Dimethylsulfoxide (DMSO)	67-68-5	>10	NT
Dimethyl Formamide	68-12-2	1-5	1-5
Salicylic acid (s) 99%	69-72-7	>480	>240
n-Propanol	71-23-8	>120	NT
Butanol	71-36-3	>480	>240
Alcohol, Amyl	71-41-0	>60	>120

Benzene	71-43-2	6-10	>30
1,1,1-Trichloroethane	71-55-6	6-10	6-10
Iodide, Methyl	74-88-4	1-5	1-5
ETHYLAMINE	75-04-7	1-5	1-5
ETHYLAMINE 70%	75-04-7	1-5	1-5
Acetonitrile	75-05-8	1-5	1-5
Acetaldehyde	75-07-0	1-5	1-5
Chloride, Methylene	75-09-2	1-5	1-5
Carbon Disulfide	75-15-0	1-5	1-5
Bromoform	75-25-2	1-5	1-5
1,1-Dichloroethene	75-35-4	1-5	1-5
Acetyl Chloride	75-36-5	1-5	1-5
Nitromethane	75-52-5	1-5	1-5
1,2-Epoxypropane	75-56-9	1-5	NT
Tetramethylammonium Hydroxide 25%	75-59-2	>480	NT
1,1,2-Trichloro-1,2,2-trifluoroethane	76-13-1	>480	>240
Dimethyl Sulfate	77-78-1	NT	>10
Citric Acid 99%	77-92-9	>480	>240
Citric Acid 30%	77-92-9	>480	>240
Citric Acid 50%	77-92-9	>480	>240
Citric Acid 75%	77-92-9	>480	>240
2-Butanol	78-83-1	>480	>240
Dichloropropane, 1,2-	78-87-5	1-5	>10
2-Butanone	78-93-3	1-5	1-5
Ethylene, Trichloride	79-01-6	1-5	6-10
2-Propenamide 50%	79-06-1	NT	>240
2-Propenamide 98%	79-06-1	>480	>240
Chloroacetic Acid 70%	79-11-8	>480	>240
Chloroacetic Acid 80%	79-11-8	>480	>240
Acetate, Methyl	79-20-9	1-5	NT
Methacrylic Acid 99%	79-41-4	>10	NT
Methacrylate, Methyl	80-62-6	6-10	NT
DBP	84-74-2	>240	NT
Vinyl Pyrrolidinone	88-12-0	6-10	6-10
Biphenyl 27%	92-52-4	6-10	NT
Dichlorobenzene O-	95-50-1	>10	>10
2-Aminotoluene	95-53-4	>30	>30

1,2,4 - Trimethyl Benzene 98%	95-63-6	>10	NT
Pseudocumene	95-63-6	>30	>60
Butanone Oxime	96-29-7	>120	>120
2-Ethylbutyl alcohol	97-95-0	>480	>240
2-Furaldehyde	98-01-1	6-10	6-10
Butyl Toluene, p-Tert	98-51-1	>480	>240
(1-Methylethyl)benzene	98-82-8	>10	>10
Nitrobenzene	98-95-3	1-5	1-5
Benzene, Ethyl	100-41-4	>10	>10
Benzene, Vinyl	100-42-5	NT	>10
Alcohol, Benzyl	100-51-6	>10	>10
Benzaldehyde	100-52-7	1-5	1-5
2,2',2''-Nitrilotriethanol	102-71-6	>30	>60
±)-2-(Chloromethyl)oxiran	106-89-8	1-5	NT
1,2-Dichloroethane	107-06-2	NT	1-5
Acrylonitrile	107-13-1	1-5	1-5
1,2-Diaminoethane 99%	107-15-3	>10	>10
2-Propen-1-ol	107-18-6	>10	>10
1,2-Ethanediol	107-21-1	>480	NT
Methyl Propyl Ketone	107-87-9	1-5	1-5
1-methoxy-2-propanol	107-98-2	>30	>60
Acetate, Vinyl	108-05-4	1-5	1-5
2-Pentanone, Methyl-	108-10-1	>10	NT
Acetate, Isopropyl	108-21-4	6-10	6-10
PROPYLENE GLYCOL MONOMETHYL ETHER ACETATE	108-65-6	>30	>30
2,6-Dimethyl-4-Heptanone	108-83-8	>60	>120
Benzene, Methyl	108-88-3	>10	>10
Benzene Chloride	108-90-7	NT	6-10
Cyclohexanol	108-93-0	>480	>240
Cyclohexanone	108-94-1	NT	>60
Carbolic Acid 89%	108-95-2	>30	>30
Carbolic Acid(s) 100%	108-95-2	>30	>30
Carbolic Acid 10%	108-95-2	>10	>10
Dimethyl Propanamide, N,N'	109-55-7	6-10	6-10
Acetate, Propyl	109-60-4	6-10	NT
Pentane	109-66-0	>480	>240
1-Aminobutane	109-73-9	6-10	6-10

DEA	109-89-7	NT	6-10
Diethylene Oxide	109-99-9	1-5	1-5
Hexane	110-54-3	>480	>240
2-Ethoxyethanol	110-80-5	6-10	NT
Cyclohexane	110-82-7	>480	>240
PYRIDINE	110-86-1	1-5	1-5
Diethylene oximide	110-91-8	1-5	1-5
1,5-Pentanedial 50%	111-30-8	>60	>120
2,2-iminodiethanol	111-42-2	>60	>60
Diethylene Glycol	111-46-6	>480	NT
n-Octane	111-65-9	>480	>240
2-Butoxyethanol	111-76-2	>240	>240
n-Octanol	111-87-5	>480	>240
Oleic Acid 98%	112-80-1	>480	NT
Oleic Acid	112-80-1	NT	>240
1,2,4-Trichlorobenzene	120-82-1	1-5	1-5
2,4-Dinitrotoluene 40%	121-14-2	>10	NT
TRIETHYLAMINE	121-44-8	>30	>120
4-Hydroxy-4-methyl-2-pentanone	123-42-2	>30	>30
3-Methyl-1-butanol	123-51-3	>480	>240
Butyl Acetate	123-86-4	1-5	NT
1,4-Dioxane	123-91-1	NT	6-10
3-Methylbutyl Ethanoate	123-92-2	1-5	1-5
Dimethylamine 40%	124-40-3	>480	>240
PERC	127-18-4	>480	>240
Dimethylacetamide N,N-	127-19-5	>10	>10
Butyl Acrylate	141-32-2	>10	>10
2-Aminoethanol	141-43-5	>60	>60
Ethyl Acetate	141-78-6	1-5	>10
Heptane	142-82-5	>480	>240
Butoxytriglycol	143-22-6	>10	>30
OXALIC ACID (s) 99%	144-62-7	480	>120
OXALIC ACID (s)	144-62-7	>480	>240
Calcium Carbonate (s) 99%	471-34-1	>480	>240
Trimethyl Phosphate	512-56-1	6-10	NT
2,2,4-Trimethyl Pentane	540-84-1	>480	>240
3-Methyl-2-Butanone	563-80-4	1-5	>10

Butyl Ethylene	592-41-6	>10	NT
Amyl Acetate	628-63-7	>10	>10
Methyl Pyrrolidone, N-	872-50-4	6-10	NT
2-Bromoethyl Acetate	927-68-4	1-5	1-5
Hexamethyldisilazane	999-97-3	NT	>240
Glyphosate Roundup 95%	1071-83-6	>480	NT
3,8-Diamino-5-ethyl-6-phenylphenanthridinium bromide 5%	1239-45-8	NT	>240
3,8-Diamino-5-ethyl-6-phenylphenanthridinium bromide 1%	1239-45-8	>480	>240
3,8-Diamino-5-ethyl-6-phenylphenanthridinium bromide 10%	1239-45-8	>480	>240
3,8-Diamino-5-ethyl-6-phenylphenanthridinium bromide 95%	1239-45-8	>480	>240
Calcium Hydroxide (s) 95%	1305-62-0	>480	>240
Iron Oxide (s) 99%	1309-37-1	>480	>240
Caustic Potash 30%	1310-58-3	>480	>240
Caustic Potash 45%	1310-58-3	>480	>240
Caustic Potash 99%	1310-58-3	>480	>240
Caustic Potash 20%	1310-58-3	>480	>240
Caustic Potash 10%	1310-58-3	>480	>240
Caustic Soda 10%	1310-73-2	>480	>240
Caustic Soda 30%	1310-73-2	>480	>240
Caustic Soda 98%	1310-73-2	>480	>240
Caustic Soda 20%	1310-73-2	>480	>240
Caustic Soda 40%	1310-73-2	>480	>240
Caustic Soda 50%	1310-73-2	>480	>240
Cresols	1319-77-3	>30	>30
Divinyl Benzene	1321-74-0	1-5	1-5
dimethyl benzene	1330-20-7	>10	NT
Chromic Acid Solution 50%	1333-82-0	1-5	NT
Ammonia Solution 29%	1336-21-6	>30	NT
Gallotannin 95%	1401-55-4	>480	>240
Gallotannin 50%	1401-55-4	>480	NT
Methyl-Tert-Butyl Ether	1634-04-4	>480	>240
2-Propoxyethanol	2807-30-9	>30	NT
Butoxypropanol	5131-66-8	>240	>240
D-Limonene	5989-27-5	>30	>30
Aluminum Chloride (s) 98%	7446-70-0	>480	>240
Potassium Chloride (s) 99%	7447-40-7	>480	>240
Hydrochloric Acid 10%	7647-01-0	NT	>240

Muriatic Acid 32%	7647-01-0	NT	>240
Muriatic Acid 20%	7647-01-0	NT	>240
Hydrochloric Acid 37%	7647-01-0	NT	>240
Sodium Chloride (s) 99%	7647-14-5	>480	>240
Phosphoric Acid 10%	7664-38-2	>480	>240
Phosphoric Acid 50%	7664-38-2	>480	>240
Phosphoric Acid 85%	7664-38-2	>480	>240
Hydrofluoric Acid 40%	7664-39-3	>30	NT
Hydrofluoric Acid 48%	7664-39-3	>10	NT
Hydrofluoric Acid 30%	7664-39-3	>120	NT
Battery Acid 93%	7664-93-9	>10	>30
Battery Acid 25%	7664-93-9	>480	>240
Battery Acid 10%	7664-93-9	>480	>240
Battery Acid 96%	7664-93-9	NT	>30
Battery Acid 47%	7664-93-9	>480	>240
Battery Acid 70%	7664-93-9	NT	>240
Battery Acid 50%	7664-93-9	>480	>240
Bleach: Sodium Hypochlorite 6%	7681-52-9	>480	NT
Nitric Acid 70%	7697-37-2	>10	NT
Nitric Acid 35%	7697-37-2	>480	>240
Nitric Acid 10%	7697-37-2	>480	>240
Nitric Acid 23%	7697-37-2	>480	>240
Nitric Acid 65%	7697-37-2	>10	NT
Nitric Acid 50%	7697-37-2	NT	>240
Hydrogen Peroxide 30%	7722-84-1	>60	NT
Iron Chloride Solution 98%	7758-94-3	>480	>240
Iron Chloride Solution 45%	7758-94-3	>480	>240
Iron Sulfate (s) 99%	7782-63-0	>480	>240
Hydroxylamine 50%	7803-49-8	NT	>240
Gasoline (unleaded)	8006-61-9	>10	NT
Fir Oil	8006-64-2	NT	>240
Kerosene	8008-20-6	>480	>240
Ligroin	8032-32-4	>30	>120
Dry Cleaning Mineral Spirits	8052-41-3	>480	>240
Hydrobromic Acid 48%	10035-10-6	>480	>240
Boric acid (s) 99%	10043-35-3	>480	>240
Calcium Chloride (s) 96%	10043-52-4	>480	>240

Tetrachloropropene	10436-39-2	>60	>120
Ammonium Fluoride 40%	12125-01-8	NT	>240
2-Chloro-2-Oxoethyl Acetate	13831-31-7	6-10	6-10
Talc (s) 99%	14807-96-6	>480	>240
Fluoboric Acid 49%	16872-11-0	>30	NT
Pentachloropropane	23153-23-3	>60	NT
Antimony Tributylate 95%	53856-17-0	NT	>240
Dry cleaning safety solvent	64475-85-0	NT	>240
Distillates (petroleum), hydrotreated light	64742-47-8	>480	>240
Mineral Spirits (White Spirits Type 3)	64742-48-9	>480	>240
Kerosene (hydrosulfurized)	64742-81-0	>480	>240
Mineral Spirits (White Spirits Type 0)	64742-88-7	>480	>240
Naphtha, light aromatic	64742-95-6	>120	NT
Diesel Oil	68334-30-5	>480	>240
Kerosene (Fuel Oil # 2)	68476-30-2	>480	>240
Diesel Fuel #2	68476-34-6	>480	>240
Mineral Spirits (odorless)	68551-17-7	>480	>240
Diesel Fuel	77650-28-3	>480	NT

BDT=BREAKTHROUGH DETECTION TIME

THE LEVEL (0 TO 6) INDICATES THE TIME REQUIRED FOR DIFFERENT CHEMICALS TO PERMEATE THROUGH THE GLOVE.

TTL : TOTAL IMMERSION CHEMICAL PERMEATION BREAKTHROUGH TIME.

INT : INTERMITTENT CONTACT CHEMICAL PERMEATION BREAKTHROUGH TIME, ONE MINUTE IMMERSION OUT OF EVERY TEN, REPEATEDLY.

Warranty Limitations and Disclaimer Use

This information is provided solely as a convenience to help you evaluate our gloves in the end-user's particular application. It is the responsibility of the purchaser and/or user to determine the level of toxicity of the materials to be handled and to select the proper glove suitable for a particular application. The information provided reflects laboratory performance of gloves under carefully controlled conditions. SHOWA makes no guarantee of results and assumes no obligation or liability in connection with this information.