

Chemical Compatibility Guide for: SHOWA 747 Nitrile Coated Gloves

The guide on the following page(s) was provided by the supplier. New Pig Corporation assumes no responsibility, obligation, or liability in conjunction with the use or misuse of the information.



New Pig

One Pork Avenue
Tipton, PA 16684-0304

newpig.com

North America: **1-800-468-4647**

Europe: **+31 (0)76 596 92 50**

China: **+86-21-400 921 5178**

PIG, PIG logo are registered trademarks in USA and other countries. See tm.newpig.com

UK: **0800 919 900**

Outside North America: **+1-814-684-0101**



747 Permeation Data

June 16, 2023

Chemical	CAS Number	TTL	INT
		ASTM F739	ASTM F1383
		BT	BT
		(minutes)	(minutes)
Acetaldehyde	75-07-0	6	NT
Acetic Acid, 5%	64-19-7	>480	>240
Acetic Acid, 10%	64-19-7	>480	>240
Acetic Acid, 25%	64-19-7	>480	>240
Acetic Acid, 50%	64-19-7	>480	>240
Acetic Acid, 84%	64-19-7	>480	>240
Acetic Acid, 99%	64-19-7	195	209
Acetone	67-64-1	11	60
Acetonitrile	75-05-8	18	NT
Acetophenone	98-86-2	24	NT
Acetoxyacetyl Chloride	13831-31-7	171	210
Acetyl Chloride	75-36-5	15	15
Acetylacetone	123-54-6	5	30
Acrylamide (s), > 98%	79-06-1	>480	>240
Acrylamide, 50%	79-06-1	>480	>240
Acrylic Acid	79-10-7	390	>240
Acrylonitrile	107-13-1	11	NT
AeroShell Fluid 41	mixture	>480	>240
Allyl Alcohol	107-18-6	160	NT
Aluminum Chloride (s), > 98%	7446-70-0	>480	>240
Aluminum Chloride, Saturated (> 45%)	7446-70-0	>480	>240
Aluminum Sulfate (s), > 99%	10043-01-3	>480	>240
Aluminum Sulfate, Saturated (> 36%)	10043-01-3	>480	>240
Ammonia, Anhydrous (gas)	7664-41-7	NR	NR
Ammonium Fluoride (s), > 98%	12125-01-8	>480	>240
Ammonium Fluoride, 80%	12125-01-8	NT	NT
Ammonium Fluoride, 40%	12125-01-8	>480	>240
Ammonium Hydroxide, 10%	1336-21-6	>480	>240
Ammonium Hydroxide, 25%	1336-21-6	>480	>240
Ammonium Hydroxide, 29%	1336-21-6	>480	>240

747 Permeation Data

Chemical	CAS Number	TTL	INT
		ASTM F739 BT (minutes)	ASTM F1383 BT (minutes)
Ammonium Hydroxide, 32%	1336-21-6	439	>240
Ammonium Nitrate (s), > 98%	6484-52-2	>480	>240
Ammonium Nitrate, Saturated (> 150%)	6484-52-2	>480	>240
Ammonium Phosphate, Dibasic (s), > 98%	7783-28-0	>480	>240
Ammonium Phosphate, Dibasic, Saturated (> 69%)	7783-28-0	>480	>240
Ammonium Phosphate, Monobasic (s), > 98%	7722-76-1	>480	>240
Ammonium Phosphate, Monobasic, Saturated (> 36%)	7722-76-1	>480	>240
Amyl Acetate	628-63-7	256	>240
Amyl Alcohol	71-41-0	> 480	> 240
Aniline	62-53-3	93	NT
Antimony Tributyrate (s), 95%	53856-17-0	>480	>240
Aqua Regia	8007-56-5	NT	NT
Benzaldehyde	100-52-7	18	54
Benzene	71-43-2	30	NT
Benzoic Acid (s), 99%	65-85-0	>480	>240
Benzoic Acid, Saturated, > 4%	65-85-0	>480	>240
Benzotrifluoride	98-08-8	83	124
Benzoyl peroxide (s), > 98%	94-36-0	>480	>240
Benzyl Alcohol	100-51-6	60	84
Boric acid, Saturated, > 4%	10043-35-3	>480	>240
Boric acid (s), > 99%	10043-35-3	>480	>240
Bromine	7726-95-6	5	NT
Bromoethyl acetate, 2-	927-68-4	6	6
Bromoform	75-25-2	10	NT
Butadiene-1,3 (gas)	106-99-0	NR	NR
Butanol, 1-	71-36-3	>480	>240
Butyl Acetate	123-86-4	128	>240
Butyl Acrylate	141-32-2	178	NT
Butyl Methacrylate	97-88-1	NT	NT
Butyl Toluene, p-tert	98-51-1	>480	>240
Butylamine	109-73-9	30	30

747 Permeation Data

<u>Chemical</u>	<u>CAS Number</u>	TTL	INT
		ASTM F739 BT (minutes)	ASTM F1383 BT (minutes)
Calcium Carbonate (s), > 99%	471-34-1	>480	>240
Calcium Chloride (s), > 96%	10043-52-4	>480	>240
Calcium Chloride, Saturated (> 75%)	10043-52-4	>480	>240
Calcium Gluconate, Anhydrous (s), > 98%	299-28-5	>480	>240
Calcium Gluconate, Saturated (> 3%)	299-28-5	>480	>240
Calcium Hydroxide (s), >95%	1305-62-0	>480	>240
Calcium Magnesium Carbonate (s), > 98%	16389-88-1	>480	>240
Calcium Oxide (s), >99%	1305-78-8	>480	>240
Calcium Phosphate Dibasic (s), > 98%	7757-93-9	>480	>240
Calcium Phosphate Dibasic Dihydrate (s), > 98%	7789-77-7	>480	>240
Calcium Sulfate (s), > 97%	7778-18-9	>480	>240
Calcium Sulfate, Saturated (> 2%)	7778-18-9	>480	>240
Carbon, mesoporous (s), > 99%	1333-86-4	>480	>240
Carbon Disulfide	75-15-0	12	12
Carbon Tetrachloride	56-23-5	>480	>240
Charcoal, activated (s), > 99%	7440-44-0	>480	>240
Chlorine (gas)	7782-50-5	NR	NR
Chloroacetic Acid, 70%	79-11-8	>480	>240
Chloroacetic Acid, 80%	79-11-8	>480	>240
Chloroacetyl Chloride	79-04-9	NT	NT
Chlorobenzene	108-90-7	30	NT
Chlorobenzotrifluoride, 4-	98-56-6	203	203
Chloroform	67-66-3	10	NT
Chromic Acid, 50%	1333-82-0	36	NT
Chromium (VI) oxide (s), 99%	1333-82-0	>480	>240
Citric Acid (s), 99%	77-92-9	>480	>240
Citric Acid, 30%	77-92-9	>480	>240
Citric Acid, 50%	77-92-9	>480	>240
Citric Acid, Saturated, >75%	77-92-9	>480	>240
Cobalt Sulfate, Heptahydrate (s), > 99%	10026-24-1	>480	>240

747 Permeation Data

Chemical	CAS Number	TTL	INT
		ASTM F739 BT (minutes)	ASTM F1383 BT (minutes)
Cobalt Sulfate, Saturated (> 36%)	10026-24-1	>480	>240
Copper Sulfate, Anhydrous (s), >98%	7758-98-7	>480	>240
Copper Sulfate, Saturated (> 20%)	7758-98-7	>480	>240
Copper Sulfate, Monohydrate (s), >98%	10257-54-2	>480	>240
Copper Sulfate, Saturated (> 20%)	10257-54-2	>480	>240
Copper Sulfate, Pentahydrate (s), >98%	7758-99-8	>480	>240
Copper Sulfate, Saturated (> 20%)	7758-99-8	>480	>240
Corn Oil	8001-30-7	NT	NT
Coolanol 25R	Mixture	>480	>240
Cresols	1319-77-3	144	171
Cumene	98-82-8	97	NT
Cyclohexane	110-82-7	>480	>240
Cyclohexanol	108-93-0	>480	>240
Cyclohexanone	108-94-1	140	NT
Cyclohexyldimethylamine	98-94-2	NT	NT
Decane	124-18-5	>480	>240
Denacol EX-521	118549-88-5	>480	>240
Diacetone Alcohol	123-42-2	165	195
Dibutyl Phthalate	84-74-2	>480	>240
Dichlorobenzene, 1,2-	95-50-1	60	NT
Dichloroethylene, 1,1-	75-35-4	1	1
Dichloropropane, 1,2-	78-87-5	42	60
Dichlorobenzotrifluoride, 3,4-	328-84-7	NT	NT
Diesel Fuel #2	68476-34-6	>480	>240
Diesel Oil	68334-30-5	>480	>240
Diestone DLS	mixture	NT	NT
Diethanolamine	111-42-2	294	>240
Diethyl Ether	60-29-7	18	18
Diethylamine	109-89-7	64	NT
Diethylene Glycol	111-46-6	>480	>240
Diethylene Glycol Monobutyl Ether	112-34-5	NT	NT

747 Permeation Data

Chemical	CAS Number	TTL	INT
		ASTM F739 BT (minutes)	ASTM F1383 BT (minutes)
Diethylene Glycol Monobutyl Ether Acetate	124-17-4	NT	NT
Diethylene Glycol Monoethyl Ether	111-90-0	NT	NT
Diethylene Glycol Monoethyl Ether Acetate	112-15-2	NT	NT
Diethylene Glycol Monohexyl Ether	112-59-4	NT	NT
Diethylene Glycol Monomethyl Ether	111-77-3	NT	NT
Diisobutyl Ketone	108-83-8	>480	>240
Dimethyl Sulfate	77-78-1	26	39
Dimethylacetamide, N,N-	127-19-5	45	45
Dimethylamine, 40%	124-40-3	> 480	> 240
Dimethylamine (gas), >99%	124-40-3	NR	NR
Dimethylaniline	121-69-7	NT	NT
Dimethylformamide-N, N	68-12-2	26	52
Dimethylpiperazine	106-58-1	NT	NT
Dimethylsulfoxide	67-68-5	476	>240
Dioxane, 1,4-	123-91-1	18	18
Dipropyl Ketone	123-19-3	NT	NT
Dipropylene Glycol Monobutyl Ether	29911-28-2	>480	>240
Dipropylene Glycol Monomethyl Ether	34590-94-8	NT	NT
Dipropylene Glycol Monopropyl Ether	29911-27-1	NT	NT
Disodium Ethylenediaminetetraacetic Acid (s), > 97%	6381-92-6	>480	>240
Disodium Ethylenediaminetetraacetic Acid, Saturated (> 10%)	6381-92-6	>480	>240
Divinylbenzene	1321-74-0	33	39
Embalming Fluid Maryland	mixture	NT	NT
Epichlorohydrin	106-89-8	27	27
Ethanol	64-17-5	>480	>240
Ethanolamine	141-43-5	225	231
Ethidium bromide (s), 95%	1239-45-8	>480	>240
Ethidium bromide, 1%	1239-45-8	>480	>240
Ethidium bromide, 10%	1239-45-8	>480	>240

747 Permeation Data

Chemical	CAS Number	TTL	INT
		ASTM F739 BT (minutes)	ASTM F1383 BT (minutes)
Ethidium bromide, 5%	1239-45-8	>480	>240
Ethyl Acetate	141-78-6	32	64
Ethyl Butanol	97-95-0	> 480	> 240
Ethyl Propyl Ketone	589-38-8	NT	NT
Ethylamine (gas), > 97%	75-04-7	NR	NR
Ethylamine solution, 70%	75-04-7	3	3
Ethylbenzene	100-41-4	76	NT
Ethylene Dichloride	107-06-2	14	NT
Ethylene Glycol	107-21-1	>480	>240
Ethylene Glycol Monobutyl Ether	111-76-2	>480	>240
Ethylene Glycol Monobutyl Ether Acetate	112-07-2	NT	NT
Ethylene Glycol Monoethyl Ether	110-80-5	NT	NT
Ethylene Glycol Monopropyl Ether	2807-30-9	NT	NT
Ethylene Oxide (gas)	75-21-8	NR	NR
Ethylenediamine, 99%	107-15-3	81	84
Ethylenediaminetetraacetic acid (s), > 98%	60-00-4	>480	>240
Everest 3.0 AG Herbicide	mixture	>480	>240
Fluoboric Acid, 49%	16872-11-0	237	NT
Formaldehyde, 37%	50-00-0	> 480	> 240
Formic Acid, 90%	64-18-6	NT	NT
Furfural	98-01-1	30	60
Gasoline (Premium Unleaded)	8032-32-4	>480	>240
Gasoline (Regular Unleaded)	8006-61-9	>480	>240
Glutaraldehyde solution, 50%	111-30-8	>480	>240
Glycerol, > 99%	56-81-5	>480	>240
Glycerol Solution, > 70%	56-81-5	>480	>240
Glyphosate (s), 95%	1071-83-6	>480	>240
Graphite (s), > 98%	7782-42-5	>480	>240
Heptane	142-82-5	> 480	> 240
Hexamethyldisilazane	999-97-3	> 480	> 240
Hexane	110-54-3	>480	>240
Hexene	592-41-6	>480	>240

747 Permeation Data

Chemical	CAS Number	TTL	INT
		ASTM F739 BT (minutes)	ASTM F1383 BT (minutes)
Hydrobromic Acid, 48%	10035-10-6	> 480	> 240
Hydrochloric Acid, 10%	7647-01-0	>480	>240
Hydrochloric Acid, 20%	7647-01-0	>480	>240
Hydrochloric Acid, 32%	7647-01-0	>480	>240
Hydrochloric Acid, 37%	7647-01-0	>480	>240
Hydrofluoric Acid, 10%	7664-39-3	>480	>240
Hydrofluoric Acid, 20%	7664-39-3	>480	>240
Hydrofluoric Acid, 30%	7664-39-3	>480	>240
Hydrofluoric Acid, 40%	7664-39-3	373	>240
Hydrofluoric Acid, 48%	7664-39-3	175	NT
Hydrogen Chloride, 99% (gas)	7647-01-0	NR	NR
Hydrogen Fluoride, 99% (gas)	7664-39-3	NR	NR
Hydrogen peroxide solution, 3%	7722-84-1	>480	>240
Hydrogen peroxide solution, 6%	7722-84-1	>480	>240
Hydrogen peroxide solution, 10%	7722-84-1	181 to 240	NT
Hydrogen peroxide solution, 30%	7722-84-1	121 to 180	NT
Hydrogen peroxide solution, 50%	7722-84-1	61 to 90	NT
Hydroxylamine, 50%	7803-49-8	>480	>240
HyJet IV-A Plus	mixture	NT	NT
HyJet V	mixture	NT	NT
Iron (II) Chloride (s), 98%	7758-94-3	>480	>240
Iron (II) Chloride Solution, 45%	7758-94-3	>480	>240
Iron (II) Chloride Solution, Saturated, >68%	7758-94-3	>480	>240
Iron (III) Chloride (s), >97%	7705-08-0	>480	>240
Iron (III) Chloride Solution, 45%	7705-08-0	>480	>240
Iron (III) Chloride Solution, Saturated, >91%	7705-08-0	>480	>240
Iron Oxide (s), 99%	1309-37-1	>480	>240
Iron (II) Sulfate (s), 99%	7782-63-0	>480	>240
Iron (II) Sulfate, Saturated (> 29%)	7782-63-0	>480	>240
Iron (III) Sulfate (s), 97%	15244-10-7	>480	>240
Iron (III) Sulfate, Saturated (> 25%)	15244-10-7	>480	>240
Isoamyl Acetate	123-92-2	21	21

747 Permeation Data

Chemical	CAS Number	TTL	INT
		ASTM F739 BT (minutes)	ASTM F1383 BT (minutes)
Isoamyl Alcohol	123-51-3	>480	>240
Isobutanol	78-83-1	>480	>240
Isooctane	540-84-1	>480	>240
Isopropyl Acetate	108-21-4	30	36
Isopropyl Alcohol	67-63-0	>480	>240
Jet A	mixture	>480	>240
Jet A-1	mixture	>480	>240
Kaolin (s), 98%	1332-58-7	>480	>240
Kerosene (Fuel Oil # 2)	68476-30-2	> 480	> 240
Kerosene (odorless)	8008-20-6	> 480	> 240
Kerosine (hydrodesulfurized)	64742-81-0	>480	>240
Lactic Acid, 85%	50-21-5	> 480	> 240
Limonene, D-	5989-27-5	126	141
Limestone, Argillaceous (s), > 98%	1317-65-3	>480	>240
Magnesium Carbonate (s), 95%	23389-33-5	>480	>240
Magnesium Chloride (s), > 97%	7786-30-3	>480	>240
Magnesium Chloride, Saturated (> 54%)	7786-30-3	>480	>240
Magnesium Hydroxide (s), > 95%	1309-42-8	>480	>240
Magnesium Oxide (s), > 95%	1309-48-4	>480	>240
Magnesium Sulfate (s), > 95%	10034-99-8	>480	>240
Magnesium Sulfate, Saturated (> 35%)	10034-99-8	>480	>240
Methacrylic Acid, 99%	79-41-4	194	NT
Methanol	67-56-1	86	>240
Methyl Acetate	79-20-9	16	56
Methyl Chloride (gas)	74-87-3	NR	NR
Methyl Ethyl Ketone	78-93-3	13	50
Methyl Ethyl Ketoxime	96-29-7	> 480	> 240
Methyl Iodide	74-88-4	1	1
Methyl Isobutyl Ketone	108-10-1	48	62
Methyl Isopropyl Ketone	563-80-4	30	NT
Methyl Methacrylate	80-62-6	17	18
Methyl Propyl Ketone	107-87-9	24	NT

747 Permeation Data

Chemical	CAS Number	TTL	INT
		ASTM F739 BT (minutes)	ASTM F1383 BT (minutes)
Methyl Tert-Butyl Ether	1634-04-4	>480	>240
Methylene Chloride	75-09-2	5	NT
Mineral Oil - Light	8042-47-5	>480	>240
Mineral Spirits (Dearomatized)	64742-47-8	> 480	> 240
Mineral Spirits (odorless)	68551-17-7	> 480	> 240
Mineral Spirits (White Spirits Type 0)	64742-88-7	>480	>240
Mineral Spirits (White Spirits Type 1)	64475-85-0	> 480	> 240
Mineral Spirits (White Spirits Type 3)	64742-48-9	> 480	> 240
Morpholine	110-91-8	1	1
Naphtha, heavy aromatic	64742-94-5	NT	NT
Naphtha, light aromatic	64742-95-6	340	> 240
Nicotine, 1% solution	54-11-5	>480	>240
Nicotine, 2% solution	54-11-5	>480	>240
Nicotine, 7% solution	54-11-5	>480	>240
Ninhydrin (s)	485-47-2	>480	>240
Nitric Acid, 10%	7697-37-2	>480	>240
Nitric Acid, 23%	7697-37-2	>480	>240
Nitric Acid, 35%	7697-37-2	>480	>240
Nitric Acid, 50%	7697-37-2	>480	>240
Nitric Acid, 65%	7697-37-2	191	191
Nitric Acid, 70%	7697-37-2	115	121
Nitrobenzene	98-95-3	12	12
Nitromethane	75-52-5	2	2
Nitropropane	79-46-9	NT	NT
N-Methyl-2-pyrrolidone	872-50-4	28	108
Octane	111-65-9	>480	>240
Octanol	111-87-5	> 480	> 240
Oleic Acid, 98%	112-80-1	> 480	> 240
Oleum (20% Free SO ₃)	8014-95-7	NT	NT
Olive Oil	8001-25-0	NT	NT
Oxalic Acid, Saturated, >10%	144-62-7	>480	>240
Oxalic Acid (s), 99%	144-62-7	> 480	> 240
Paraffin Oil	8012-95-1	>480	>240

747 Permeation Data

<u>Chemical</u>	<u>CAS Number</u>	TTL	INT
		ASTM F739 BT (minutes)	ASTM F1383 BT (minutes)
Pentachloropropane	23153-23-3	NT	NT
Pentane	109-66-0	>480	>240
Peracetic acid solution, 39%	79-21-0	NT	NT
Perchloric Acid, 70%	7601-90-3	NT	NT
Petroleum Benzene	64742-49-0	>480	>240
Petroleum Ether	68476-50-6	>480	>240
Phenol (s), ~100%	108-95-2	180	180
Phenol, > 89%	108-95-2	120	120
Phenol, 10%	108-95-2	150	150
Phosphoric Acid, 5%	7664-38-2	>480	>240
Phosphoric Acid, 10%	7664-38-2	> 480	> 240
Phosphoric Acid, 15%	7664-38-2	>480	>240
Phosphoric Acid, 20%	7664-38-2	>480	>240
Phosphoric Acid, 25%	7664-38-2	>480	>240
Phosphoric Acid, 30%	7664-38-2	>480	>240
Phosphoric Acid, 35%	7664-38-2	>480	>240
Phosphoric Acid, 40%	7664-38-2	>480	>240
Phosphoric Acid, 45%	7664-38-2	>480	>240
Phosphoric Acid, 50%	7664-38-2	> 480	> 240
Phosphoric Acid, 55%	7664-38-2	>480	>240
Phosphoric Acid, 60%	7664-38-2	>480	>240
Phosphoric Acid, 65%	7664-38-2	>480	>240
Phosphoric Acid, 70%	7664-38-2	>480	>240
Phosphoric Acid, 75%	7664-38-2	>480	>240
Phosphoric Acid, 80%	7664-38-2	>480	>240
Phosphoric Acid, 85%	7664-38-2	> 480	> 240
Phosphoric Acid (s), 99%	7664-38-2	>480	>240
Polyethylene Glycol (s), > 98%	25322-68-3	>480	>240
Polyethylene Glycol, Saturated (> 67 %)	25322-68-3	>480	>240
Potassium Bicarbonate (s), > 99%	298-14-6	>480	>240
Potassium Bicarbonate, Saturated (> 36%)	298-14-6	>480	>240
Potassium Bisulfite (s), > 95%	7773-03-7	>480	>240

747 Permeation Data

Chemical	CAS Number	TTL	INT
		ASTM F739 BT (minutes)	ASTM F1383 BT (minutes)
Potassium Bisulfite, Saturated (> 49%)	7773-03-7	>480	>240
Potassium Carbonate (s), >98%	584-08-7	>480	>240
Potassium Carbonate, Saturated (> 138%)	584-08-7	>480	>240
Potassium Chloride (s), 99%	7447-40-7	> 480	> 240
Potassium Chloride, Saturated (> 35%)	7447-40-7	>480	>240
Potassium Hydroxide (s), 99%	1310-58-3	> 480	> 240
Potassium Hydroxide, 5%	1310-58-3	>480	>240
Potassium Hydroxide, 10%	1310-58-3	> 480	> 240
Potassium Hydroxide, 15%	1310-58-3	>480	>240
Potassium Hydroxide, 20%	1310-58-3	> 480	> 240
Potassium Hydroxide, 25%	1310-58-3	>480	>240
Potassium Hydroxide, 30%	1310-58-3	> 480	> 240
Potassium Hydroxide, 35%	1310-58-3	>480	>240
Potassium Hydroxide, 40%	1310-58-3	>480	>240
Potassium Hydroxide, 45%	1310-58-3	> 480	> 240
Potassium Hydroxide, 50%	1310-58-3	>480	>240
Potassium Hydroxide, 54%	1310-58-3	>480	>240
Potassium Permanganate (s), > 99%	7722-64-7	>480	>240
Potassium Permanganate, Saturated (> 76%)	7722-64-7	>480	>240
Propanediamine, N,N'-Dimethyl	109-55-7	74	74
Propanol, 1-	71-23-8	>480	> 240
Propyl Acetate	109-60-4	64	235
Propylene Glycol	57-55-6	> 480	> 240
Propylene Glycol Monobutyl Ether	5131-66-8	> 480	> 240
Propylene Glycol Monomethyl Ether	107-98-2	184	> 240
Propylene Glycol Monomethyl Ether Acetate	108-65-6	88	154
Propylene Glycol Monopropyl Ether	1569-01-3	NT	NT
Propylene Oxide	75-56-9	2	2
Pyridine	110-86-1	6	6
Quartz (s), 99%	14808-60-7	> 480	> 240

747 Permeation Data

<u>Chemical</u>	<u>CAS Number</u>	TTL	INT
		ASTM F739 BT (minutes)	ASTM F1383 BT (minutes)
Salicylic acid (s), 99%	69-72-7	> 480	> 240
Screen Wash Universal (ZT639)	mixture	NT	NT
Selenium Sulfide (s), 99%	7488-56-4	> 480	>240
Skydrol 500B-4	mixture	> 480	>240
Skydrol LD-4	mixture	> 480	>240
Silicon Dioxide (s), 99%	7631-86-9	> 480	>240
Sodium Bicarbonate (s), 99%	144-55-8	> 480	>240
Sodium Bicarbonate, Saturated (> 10%)	144-55-8	> 480	>240
Sodium Bisulfite (s), > 95%	7631-90-5	> 480	>240
Sodium Bisulfite, Saturated (> 42%)	7631-90-5	> 480	>240
Sodium Tetraborate Decahydrate (s), > 99%	1303-96-4	> 480	>240
Sodium Tetraborate Decahydrate, Saturated (> 49%)	1303-96-4	> 480	>240
Sodium Carbonate (s), 99%	497-19-8	> 480	>240
Sodium Carbonate, Saturated (> 9%)	497-19-8	> 480	>240
Sodium Chloride (s), 99%	7647-14-5	> 480	> 240
Sodium Chloride, Saturated (> 36%)	7647-14-5	> 480	>240
Sodium Lauryl Sulfate (s), > 90%	151-21-3	> 480	>240
Sodium Lauryl Sulfate, Saturated (> 15%)	151-21-3	> 480	>240
Sodium Fluoride (s), > 99%	7681-49-4	> 480	>240
Sodium Fluoride, Saturated (> 4%)	7681-49-4	> 480	>240
Sodium Gluconate (s), > 98%	527-07-1	> 480	>240
Sodium Gluconate, Saturated (> 59%)	527-07-1	> 480	>240
Sodium Hydroxide (s), 98%	1310-73-2	> 480	> 240
Sodium Hydroxide, 5%	1310-73-2	> 480	>240
Sodium Hydroxide, 10%	1310-73-2	> 480	> 240
Sodium Hydroxide, 15%	1310-73-2	> 480	>240
Sodium Hydroxide, 20%	1310-73-2	> 480	> 240
Sodium Hydroxide, 25%	1310-73-2	> 480	>240
Sodium Hydroxide, 30%	1310-73-2	> 480	> 240
Sodium Hydroxide, 35%	1310-73-2	> 480	>240

747 Permeation Data

<u>Chemical</u>	<u>CAS Number</u>	TTL	INT
		ASTM F739 BT (minutes)	ASTM F1383 BT (minutes)
Sodium Hydroxide, 40%	1310-73-2	> 480	> 240
Sodium Hydroxide, 45%	1310-73-2	> 480	>240
Sodium Hydroxide, 50%	1310-73-2	> 480	> 240
Sodium Hypochlorite, 12%	7681-52-9	> 480	> 240
Sodium Hypochlorite, 6%	7681-52-9	> 480	> 240
Sodium Metabisulfite (s), > 97%	7681-57-4	> 480	>240
Sodium Metasilicate (s), > 98%	6834-92-0	> 480	>240
Sodium Metasilicate, Saturated (> 21%)	6834-92-0	> 480	>240
Sodium Nitrite (s), > 97%	7632-00-0	> 480	>240
Sodium Nitrite, Saturated (> 82%)	7632-00-0	> 480	>240
Sodium Permanganate (s), > 95%	10101-50-5	> 480	>240
Sodium Permanganate Solution, 40%	10101-50-5	> 480	>240
Sodium Selenite (s), > 98%	10102-18-8	> 480	>240
Sodium Selenite, Saturated (> 89%)	10102-18-8	> 480	>240
Sodium Sulfate (s), > 99%	7757-82-6	> 480	>240
Sodium Sulfate, Saturated (> 28%)	7757-82-6	> 480	>240
Sodium Sulfite (s), > 98%	7757-83-7	> 480	>240
Sodium Sulfite, Saturated (> 27%)	7757-83-7	> 480	>240
Sodium Thiosulfate (s), > 98%	7772-98-7	> 480	>240
Sodium Thiosulfate, Saturated (> 70%)	7772-98-7	> 480	>240
Soybean oil	8001-22-7	NT	NT
Stoddard Solvent	8052-41-3	> 480	>240
Styrene	100-42-5	11	16
Sulfuric Acid, 10%	7664-93-9	>480	>240
Sulfuric Acid, 15%	7664-93-9	> 480	>240
Sulfuric Acid, 18%	7664-93-9	> 480	>240
Sulfuric Acid, 25%	7664-93-9	>480	>240
Sulfuric Acid, 30%	7664-93-9	> 480	>240
Sulfuric Acid, 39%	7664-93-9	> 480	>240
Sulfuric Acid, 47%	7664-93-9	>480	>240
Sulfuric Acid, 50%	7664-93-9	>480	>240

747 Permeation Data

Chemical	CAS Number	TTL	INT
		ASTM F739 BT (minutes)	ASTM F1383 BT (minutes)
Sulfuric Acid, 70%	7664-93-9	>480	>240
Sulfuric Acid, 93%	7664-93-9	186	207
Sulfuric Acid, 96%	7664-93-9	186	207
Talc (s), >99%	14807-96-6	> 480	> 240
Tannic Acid (s), 95%	1401-55-4	> 480	> 240
Tetrachloroethylene	127-18-4	>480	> 240
Tetrachloropropene	10436-39-2	200	NT
Tetrahydrofuran	109-99-9	8	8
Tetramethylammonium Hydroxide, 25%	75-59-2	>480	>240
Titanium Dioxide (s), > 99%	13463-67-7	>480	>240
Toluene	108-88-3	38	58
Toluene-2,4-diisocyanate	584-84-9	>480	>240
Toluene-2,6-diisocyanate	91-08-7	>480	>240
Toluidine, O-	95-53-4	96	NT
Tricalcium Phosphate (s), > 95%	7758-87-4	>480	>240
Trichlorobenzene, 1,2,4-	120-82-1	31	NT
Trichloroethylene	79-01-6	24	42
Tricresyl Phosphate	1330-78-5	>480	>240
Triethanolamine	102-71-6	> 480	> 240
Triethylamine	121-44-8	92	>240
Triethylene Glycol Monobutyl Ether	143-22-6	64	76
Triethylene Glycol Monoethyl Ether	112-50-5	>480	>240
Triethylene Glycol Monomethyl Ether	112-35-6	>480	>240
Trimethyl Phosphate	512-56-1	24	NT
Trimethylbenzene	95-63-6	98	NT
Turpentine	8006-64-2	> 480	> 240
Urea Solution, 30 to 35%	57-13-6	>480	>240
Urea, Saturated Solution, >62%	57-13-6	>480	>240
Urea (s), 99%	57-13-6	> 480	> 240
Vinyl Acetate	108-05-4	64	235
Vinyl Pyrrolidinone	88-12-0	14	54
VM&P Naphtha	8030-30-6	> 480	> 240



747 Permeation Data

<u>Chemical</u>	<u>CAS Number</u>	TTL	INT
		ASTM F739 BT (minutes)	ASTM F1383 BT (minutes)
Xylene	1330-20-7	96	NT
Zinc (s), >98%	7440-66-6	>480	>240
Zinc Oxide (s), >99%	1314-13-2	>480	>240
Zinc Sulfate, Heptahydrate (s), >99%	7446-20-0	>480	>240
Zinc Sulfate, Saturated (> 96%)	7446-20-0	>480	>240
Zinc Sulfate, Monohydrate (s), >99%	7446-19-7	>480	>240
Zinc Sulfate, Saturated (> 35%)	7446-19-7	>480	>240

Permeation Legend and Explanation

Permeation is the act of a chemical passing through a solid material, such as personal protective clothing, on a molecular level.

TTL : Total immersion chemical permeation breakthrough time (maximum test duration of 480 minutes).

INT : Intermittent contact chemical permeation breakthrough time, one minute immersion out of every ten minutes repeatedly, up to maximum test duration of 240 minutes.

The information provided in this chart is intended to help you determine the general suitability of SHOWA gloves in the end-user’s particular application. It is the responsibility of the purchaser and/or user to determine the level of toxicity of the materials to be handled and to select the proper glove suitable for a particular application. The information provided reflects laboratory performance of gloves under carefully controlled conditions. SHOWA makes no guarantee of results and assumes no obligation or liability in connection with this information.