

# Chemical Compatibility Guide for: SHOWA N8 Neoprene Gloves

The guide on the following page(s) was provided by the supplier. New Pig Corporation assumes no responsibility, obligation, or liability in conjunction with the use or misuse of the information.



**New Pig**

One Pork Avenue  
Tipton, PA 16684-0304

**newpig.com**

North America: **1-800-468-4647**

Europe: **+31 (0)76 596 92 50**

China: **+86-21-400 921 5178**

PIG, PIG logo are registered trademarks in USA and other countries. See [tm.newpig.com](http://tm.newpig.com)

UK: **0800 919 900**

Outside North America: **+1-814-684-0101**



## Showa N8 Permeation Data

June 15, 2023

Chemical	CAS Number	TTL	TTL	INT
		ASTM F739 BT (minutes)	EN 374 BT (minutes)	ASTM F1383 BT (minutes)
Acetaldehyde	75-07-0	NT	NT	NT
Acetic Acid, 5%	64-19-7	>480	> 480	> 240
Acetic Acid, 10%	64-19-7	>480	> 480	> 240
Acetic Acid, 25%	64-19-7	>480	> 480	> 240
Acetic Acid, 50%	64-19-7	>480	> 480	> 240
Acetic Acid, 84%	64-19-7	>480	> 480	> 240
Acetic Acid, 99%	64-19-7	>480	> 480	> 240
Acetone	67-64-1	33	32	98
Acetonitrile	75-05-8	96	100	NT
Acetophenone	98-86-2	28	26	NT
Acetoxyacetyl Chloride	13831-31-7	NT	NT	NT
Acetyl Chloride	75-36-5	NT	NT	NT
Acetylacetone	123-54-6	NT	NT	NT
Acrylamide (s), > 98%	79-06-1	> 480	> 480	> 240
Acrylamide, 50%	79-06-1	> 480	> 480	> 240
Acrylic Acid	79-10-7	NT	NT	NT
Acrylonitrile	107-13-1	52	52	NT
AeroShell Fluid 41	mixture	NT	NT	NT
Allyl Alcohol	107-18-6	> 480	> 480	> 240
Aluminum Chloride (s), > 98%	7446-70-0	> 480	> 480	> 240
Aluminum Chloride, Saturated (> 45%)	7446-70-0	> 480	> 480	> 240
Aluminum Sulfate (s), > 99%	10043-01-3	> 480	> 480	> 240
Aluminum Sulfate, Saturated (> 36%)	10043-01-3	> 480	> 480	> 240
Ammonia, Anhydrous (gas)	7664-41-7	NR	NR	NR
Ammonium Fluoride (s), > 98%	12125-01-8	> 480	> 480	> 240
Ammonium Fluoride, 80%	12125-01-8	> 480	> 480	> 240
Ammonium Fluoride, 40%	12125-01-8	> 480	> 480	> 240
Ammonium Hydroxide, 10%	1336-21-6	> 480	> 480	> 240
Ammonium Hydroxide, 25%	1336-21-6	> 480	> 480	> 240
Ammonium Hydroxide, 29%	1336-21-6	> 480	> 480	> 240

**Showa N8 Permeation Data**

Chemical	CAS Number	TTL	TTL	INT
		ASTM F739	EN 374	ASTM F1383
		BT	BT	BT
		(minutes)	(minutes)	(minutes)
Ammonium Hydroxide, 32%	1336-21-6	> 480	> 480	> 240
Ammonium Nitrate (s), > 98%	6484-52-2	> 480	> 480	> 240
Ammonium Nitrate, Saturated (> 150%)	6484-52-2	> 480	> 480	> 240
Ammonium Phosphate, Dibasic (s), > 98%	7783-28-0	> 480	> 480	> 240
Ammonium Phosphate, Dibasic, Saturated (> 69%)	7783-28-0	> 480	> 480	> 240
Ammonium Phosphate, Monobasic (s), > 98%	7722-76-1	> 480	> 480	> 240
Ammonium Phosphate, Monobasic, Saturated (> 36%)	7722-76-1	> 480	> 480	> 240
Amyl Acetate	628-63-7	NT	NT	NT
Amyl Alcohol	71-41-0	> 480	> 480	> 240
Aniline	62-53-3	NT	NT	NT
Antimony Tributyrate (s), 95%	53856-17-0	> 480	> 480	> 240
Aqua Regia	8007-56-5	> 480	> 480	> 240
Benzaldehyde	100-52-7	NT	NT	NT
Benzene	71-43-2	NT	NT	NT
Benzoic Acid (s), 99%	65-85-0	> 480	> 480	> 240
Benzoic Acid, Saturated, > 4%	65-85-0	> 480	> 480	> 240
Benzotrifluoride	98-08-8	NT	NT	NT
Benzoyl peroxide (s), > 98%	94-36-0	> 480	> 480	> 240
Benzyl Alcohol	100-51-6	> 480	> 480	> 240
Boric acid, Saturated, > 4%	10043-35-3	> 480	> 480	> 240
Boric acid (s), > 99%	10043-35-3	> 480	> 480	> 240
Bromine	7726-95-6	7	6	NT
Bromoethyl acetate, 2-	927-68-4	NT	NT	NT
Bromoform	75-25-2	14	13	NT
Butadiene-1,3 (gas)	106-99-0	NT	NT	NT
Butanol, 1-	71-36-3	> 480	> 480	> 240
Butyl Acetate	123-86-4	NT	NT	NT
Butyl Acrylate	141-32-2	66	62	NT

**Showa N8 Permeation Data**

Chemical	CAS Number	TTL	TTL	INT
		ASTM F739	EN 374	ASTM F1383
		BT	BT	BT
		(minutes)	(minutes)	(minutes)
Butyl Methacrylate	97-88-1	NT	NT	NT
Butyl Toluene, p-tert	98-51-1	> 480	> 480	> 240
Butylamine	109-73-9	NT	NT	NT
Calcium Carbonate (s), > 99%	471-34-1	> 480	> 480	> 240
Calcium Chloride (s), > 96%	10043-52-4	> 480	> 480	> 240
Calcium Chloride, Saturated (> 75%)	10043-52-4	> 480	> 480	> 240
Calcium Gluconate, Anhydrous (s), > 98%	299-28-5	> 480	> 480	> 240
Calcium Gluconate, Saturated (> 3%)	299-28-5	> 480	> 480	> 240
Calcium Hydroxide (s), >95%	1305-62-0	> 480	> 480	> 240
Calcium Magnesium Carbonate (s), > 98%	16389-88-1	> 480	> 480	> 240
Calcium Oxide (s), >99%	1305-78-8	> 480	> 480	> 240
Calcium Phosphate Dibasic (s), > 98%	7757-93-9	> 480	> 480	> 240
Calcium Phosphate Dibasic Dihydrate (s), > 98%	7789-77-7	> 480	> 480	> 240
Calcium Sulfate (s), > 97%	7778-18-9	> 480	> 480	> 240
Calcium Sulfate, Saturated (> 2%)	7778-18-9	> 480	> 480	> 240
Carbon, mesoporous (s), > 99%	1333-86-4	> 480	> 480	> 240
Carbon Disulfide	75-15-0	NT	NT	NT
Carbon Tetrachloride	56-23-5	60	60	NT
Charcoal, activated (s), > 99%	7440-44-0	>480	>480	>240
Chlorine (gas)	7782-50-5	NT	NT	NT
Chloroacetic Acid, 70%	79-11-8	> 480	> 480	> 240
Chloroacetic Acid, 80%	79-11-8	> 480	> 480	> 240
Chloroacetyl Chloride	79-04-9	NT	NT	NT
Chlorobenzene	108-90-7	NT	NT	NT
Chlorobenzotrifluoride, 4-	98-56-6	NT	NT	NT
Chloroform	67-66-3	14	13	34
Chromic Acid, 50%	1333-82-0	NT	NT	NT
Chromium (VI) oxide (s), 99%	1333-82-0	> 480	> 480	> 240
Citric Acid (s), 99%	77-92-9	> 480	> 480	> 240



**Showa N8 Permeation Data**

Chemical	CAS Number	TTL	TTL	INT
		ASTM F739	EN 374	ASTM F1383
		BT	BT	BT
		(minutes)	(minutes)	(minutes)
Citric Acid, 30%	77-92-9	> 480	> 480	> 240
Citric Acid, 50%	77-92-9	> 480	> 480	> 240
Citric Acid, Saturated, >75%	77-92-9	> 480	> 480	> 240
Cobalt Sulfate, Heptahydrate (s), > 99%	10026-24-1	> 480	> 480	> 240
Cobalt Sulfate, Saturated (> 36%)	10026-24-1	> 480	> 480	> 240
Copper Sulfate, Anhydrous (s), >98%	7758-98-7	> 480	> 480	> 240
Copper Sulfate, Saturated (> 20%)	7758-98-7	> 480	> 480	> 240
Copper Sulfate, Monohydrate (s), >98%	10257-54-2	> 480	> 480	> 240
Copper Sulfate, Saturated (> 20%)	10257-54-2	> 480	> 480	> 240
Copper Sulfate, Pentahydrate (s), >98%	7758-99-8	> 480	> 480	> 240
Copper Sulfate, Saturated (> 20%)	7758-99-8	> 480	> 480	> 240
Corn Oil	8001-30-7	NT	NT	NT
Coolanol 25R	Mixture	NT	NT	NT
Cresols	1319-77-3	NT	NT	NT
Cumene	98-82-8	NT	NT	NT
Cyclohexane	110-82-7	268	227	>240
Cyclohexanol	108-93-0	>480	>480	> 240
Cyclohexanone	108-94-1	103	88	> 240
Cyclohexyldimethylamine	98-94-2	NT	NT	NT
Denacol EX-521	118549-88-5	NT	NT	NT
Diacetone Alcohol	123-42-2	NT	NT	NT
Dibutyl Phthalate	84-74-2	NT	NT	NT
Dichlorobenzene, 1,2-	95-50-1	NT	NT	NT
Dichloroethylene, 1,1-	75-35-4	NT	NT	NT
Dichloropropane, 1,2-	78-87-5	34	33	62
Dichlorobenzotrifluoride, 3,4-	328-84-7	NT	NT	NT
Diesel Fuel #2	68476-34-6	>480	>480	>240
Diesel Oil	68334-30-5	>480	>480	>240
Diestone DLS	mixture	NT	NT	NT

**Showa N8 Permeation Data**

Chemical	CAS Number	TTL	TTL	INT
		ASTM F739	EN 374	ASTM F1383
		BT	BT	BT
		(minutes)	(minutes)	(minutes)
Diethanolamine	111-42-2	>480	>480	>240
Diethyl Ether	60-29-7	NT	NT	NT
Diethylamine	109-89-7	24	21	NT
Diethylene Glycol	111-46-6	NT	NT	NT
Diethylene Glycol Monobutyl Ether	112-34-5	NT	NT	NT
Diethylene Glycol Monobutyl Ether Acetate	124-17-4	NT	NT	NT
Diethylene Glycol Monoethyl Ether	111-90-0	NT	NT	NT
Diethylene Glycol Monoethyl Ether Acetate	112-15-2	NT	NT	NT
Diethylene Glycol Monohexyl Ether	112-59-4	NT	NT	NT
Diethylene Glycol Monomethyl Ether	111-77-3	NT	NT	NT
Diisobutyl Ketone	108-83-8	NT	NT	NT
Dimethyl Sulfate	77-78-1	NT	NT	NT
Dimethylacetamide, N,N-	127-19-5	NT	NT	NT
Dimethylamine, 40%	124-40-3	62	NT	NT
Dimethylamine (gas), >99%	124-40-3	NT	NT	NT
Dimethylaniline	121-69-7	NT	NT	NT
Dimethylformamide-N, N	68-12-2	200	92	>240
Dimethylpiperazine	106-58-1	NT	NT	NT
Dimethylsulfoxide	67-68-5	>480	>480	>240
Dioxane, 1,4-	123-91-1	NT	NT	NT
Dipropyl Ketone	123-19-3	NT	NT	NT
Dipropylene Glycol Monobutyl Ether	29911-28-2	NT	NT	NT
Dipropylene Glycol Monomethyl Ether	34590-94-8	NT	NT	NT
Dipropylene Glycol Monopropyl Ether	29911-27-1	NT	NT	NT
Disodium Ethylenediaminetetraacetic Acid (s), > 97%	6381-92-6	>480	>480	> 240
Disodium Ethylenediaminetetraacetic Acid, Saturated (> 10%)	6381-92-6	>480	>480	> 240
Divinylbenzene	1321-74-0	NT	NT	NT
Embalming Fluid Maryland	mixture	NT	NT	NT

**Showa N8 Permeation Data**

Chemical	CAS Number	TTL	TTL	INT
		ASTM F739	EN 374	ASTM F1383
		BT	BT	BT
		(minutes)	(minutes)	(minutes)
Epichlorohydrin	106-89-8	NT	NT	NT
Ethanol	64-17-5	>480	>480	> 240
Ethanolamine	141-43-5	NT	NT	NT
Ethidium bromide (s), 95%	1239-45-8	>480	>480	>240
Ethidium bromide, 1%	1239-45-8	>480	>480	>240
Ethidium bromide, 10%	1239-45-8	>480	>480	>240
Ethidium bromide, 5%	1239-45-8	>480	>480	>240
Ethyl Acetate	141-78-6	32	30	NT
Ethyl Butanol	97-95-0	>480	>480	>240
Ethyl Propyl Ketone	589-38-8	NT	NT	NT
Ethylamine (gas), > 97%	75-04-7	NT	NT	NT
Ethylamine solution, 70%	75-04-7	NT	NT	NT
Ethylbenzene	100-41-4	NT	NT	NT
Ethylene Dichloride	107-06-2	23	21	NT
Ethylene Glycol	107-21-1	>480	>480	>240
Ethylene Glycol Monobutyl Ether	111-76-2	NT	NT	NT
Ethylene Glycol Monobutyl Ether Acetate	112-07-2	NT	NT	NT
Ethylene Glycol Monoethyl Ether	110-80-5	>480	>480	>240
Ethylene Glycol Monopropyl Ether	2807-30-9	NT	NT	NT
Ethylene Oxide (gas)	75-21-8	NT	NT	NT
Ethylenediamine, 99%	107-15-3	NT	NT	NT
Ethylenediaminetetraacetic acid (s), > 98%	60-00-4	>480	>480	> 240
Everest 3.0 AG Herbicide	mixture	NT	NT	NT
Fluoboric Acid, 49%	16872-11-0	>480	>480	>240
Formaldehyde, 37%	50-00-0	176	> 480	NT
Formic Acid, 90%	64-18-6	>480	>480	>240
Furfural	98-01-1	NT	NT	NT
Gasoline (Premium Unleaded)	8032-32-4	>480	>480	>240
Gasoline (Regular Unleaded)	8006-61-9	>480	>480	>240

**Showa N8 Permeation Data**

Chemical	CAS Number	TTL	TTL	INT
		ASTM F739	EN 374	ASTM F1383
		BT	BT	BT
		(minutes)	(minutes)	(minutes)
Glutaraldehyde solution, 50%	111-30-8	>480	>480	> 240
Glycerol, > 99%	56-81-5	>480	>480	>240
Glycerol Solution, > 70%	56-81-5	>480	>480	>240
Glyphosate (s), 95%	1071-83-6	>480	>480	>240
Graphite (s), > 98%	7782-42-5	>480	>480	>240
Heptane	142-82-5	212	268	NT
Hexamethyldisilazane	999-97-3	NT	NT	NT
Hexane	110-54-3	168	148	NT
Hexene	592-41-6	NT	NT	NT
Hydrobromic Acid, 48%	10035-10-6	>480	>480	> 240
Hydrochloric Acid, 10%	7647-01-0	>480	>480	> 240
Hydrochloric Acid, 20%	7647-01-0	>480	>480	>240
Hydrochloric Acid, 32%	7647-01-0	>480	>480	>240
Hydrochloric Acid, 37%	7647-01-0	>480	>480	> 240
Hydrofluoric Acid, 10%	7664-39-3	>480	>480	>240
Hydrofluoric Acid, 20%	7664-39-3	>480	>480	>240
Hydrofluoric Acid, 30%	7664-39-3	>480	>480	>240
Hydrofluoric Acid, 40%	7664-39-3	>480	>480	>240
Hydrofluoric Acid, 48%	7664-39-3	>480	>480	>240
Hydrogen Chloride, 99% (gas)	7647-01-0	>480	>480	>240
Hydrogen Fluoride, 99% (gas)	7664-39-3	>480	>480	>240
Hydrogen peroxide solution, 3%	7722-84-1	NT	NT	NT
Hydrogen peroxide solution, 6%	7722-84-1	NT	NT	NT
Hydrogen peroxide solution, 10%	7722-84-1	NT	NT	NT
Hydrogen peroxide solution, 30%	7722-84-1	NT	NT	NT
Hydrogen peroxide solution, 50%	7722-84-1	NT	NT	NT
Hydroxylamine, 50%	7803-49-8	>480	>480	>240
HyJet IV-A Plus	mixture	NT	NT	NT
HyJet V	mixture	NT	NT	NT
Iron (II) Chloride (s), 98%	7758-94-3	>480	>480	>240





**Showa N8 Permeation Data**

Chemical	CAS Number	TTL	TTL	INT
		ASTM F739	EN 374	ASTM F1383
		BT	BT	BT
		(minutes)	(minutes)	(minutes)
Iron (II) Chloride Solution, 45%	7758-94-3	>480	>480	>240
Iron (II) Chloride Solution, Saturated, >68%	7758-94-3	>480	>480	>240
Iron (III) Chloride (s), >97%	7705-08-0	>480	>480	>240
Iron (III) Chloride Solution, 45%	7705-08-0	>480	>480	>240
Iron (III) Chloride Solution, Saturated, >91%	7705-08-0	>480	>480	>240
Iron Oxide (s), 99%	1309-37-1	>480	>480	>240
Iron (II) Sulfate (s), 99%	7782-63-0	>480	>480	>240
Iron (II) Sulfate, Saturated (> 29%)	7782-63-0	>480	>480	>240
Iron (III) Sulfate (s), 97%	15244-10-7	>480	>480	>240
Iron (III) Sulfate, Saturated (> 25%)	15244-10-7	>480	>480	>240
Isoamyl Acetate	123-92-2	NT	NT	NT
Isoamyl Alcohol	123-51-3	>480	>480	> 240
Isobutanol	78-83-1	>480	>480	> 240
Isooctane	540-84-1	NT	NT	NT
Isopropyl Acetate	108-21-4	NT	NT	NT
Isopropyl Alcohol	67-63-0	>480	>480	> 240
Jet A	mixture	NT	NT	NT
Jet A-1	mixture	NT	NT	NT
Kaolin (s), 98%	1332-58-7	>480	>480	>240
Kerosene (Fuel Oil # 2)	68476-30-2	>480	>480	> 240
Kerosene (odorless)	8008-20-6	>480	>480	> 240
Kerosine (hydrodesulfurized)	64742-81-0	>480	>480	> 240
Lactic Acid, 85%	50-21-5	>480	>480	> 240
Limonene, D-	5989-27-5	NT	NT	NT
Limestone, Argillaceous (s), > 98%	1317-65-3	>480	>480	>240
Magnesium Carbonate (s), 95%	23389-33-5	>480	>480	>240
Magnesium Chloride (s), > 97%	7786-30-3	>480	>480	>240
Magnesium Chloride, Saturated (> 54%)	7786-30-3	>480	>480	>240
Magnesium Hydroxide (s), > 95%	1309-42-8	>480	>480	>240



**Showa N8 Permeation Data**

Chemical	CAS Number	TTL	TTL	INT
		ASTM F739	EN 374	ASTM F1383
		BT	BT	BT
		(minutes)	(minutes)	(minutes)
Magnesium Oxide (s), > 95%	1309-48-4	>480	>480	>240
Magnesium Sulfate (s), > 95%	10034-99-8	>480	>480	>240
Magnesium Sulfate, Saturated (> 35%)	10034-99-8	>480	>480	>240
Methacrylic Acid, 99%	79-41-4	NT	NT	NT
Methanol	67-56-1	212	448	>240
Methyl Acetate	79-20-9	NT	NT	NT
Methyl Chloride (gas)	74-87-3	NT	NT	NT
Methyl Ethyl Ketone	78-93-3	32	27	52
Methyl Ethyl Ketoxime	96-29-7	> 480	> 480	> 240
Methyl Iodide	74-88-4	NT	NT	NT
Methyl Isobutyl Ketone	108-10-1	57	46	60
Methyl Isopropyl Ketone	563-80-4	34	30	NT
Methyl Methacrylate	80-62-6	NT	NT	NT
Methyl Propyl Ketone	107-87-9	28	26	NT
Methyl Tert-Butyl Ether	1634-04-4	60	63	NT
Methylene Chloride	75-09-2	9	8	27
Mineral Oil - Light	8042-47-5	>480	> 480	> 240
Mineral Spirits (Dearomatized)	64742-47-8	>480	> 480	> 240
Mineral Spirits (odorless)	68551-17-7	>480	> 480	> 240
Mineral Spirits (White Spirits Type 0)	64742-88-7	> 480	> 480	> 240
Mineral Spirits (White Spirits Type 1)	64475-85-0	>480	> 480	> 240
Mineral Spirits (White Spirits Type 3)	64742-48-9	>480	> 480	> 240
Morpholine	110-91-8	NT	NT	NT
Naphtha, heavy aromatic	64742-94-5	25	21	NT
Naphtha, light aromatic	64742-95-6	50	42	NT
Nicotine, 1% solution	54-11-5	NT	NT	NT
Nicotine, 2% solution	54-11-5	NT	NT	NT
Nicotine, 7% solution	54-11-5	NT	NT	NT
Ninhydrin (s)	485-47-2	> 480	> 480	>240
Nitric Acid, 10%	7697-37-2	> 480	> 480	> 240

**Showa N8 Permeation Data**

Chemical	CAS Number	TTL	TTL	INT
		ASTM F739	EN 374	ASTM F1383
		BT	BT	BT
		(minutes)	(minutes)	(minutes)
Nitric Acid, 23%	7697-37-2	> 480	> 480	> 240
Nitric Acid, 35%	7697-37-2	> 480	> 480	> 240
Nitric Acid, 50%	7697-37-2	> 480	> 480	> 240
Nitric Acid, 65%	7697-37-2	> 480	> 480	> 240
Nitric Acid, 70%	7697-37-2	> 480	> 480	> 240
Nitrobenzene	98-95-3	NT	NT	NT
Nitromethane	75-52-5	NT	NT	NT
Nitropropane	79-46-9	NT	NT	NT
N-Methyl-2-pyrrolidone	872-50-4	NT	NT	NT
Octane	111-65-9	364	428	>240
Octanol	111-87-5	>480	>480	>240
Oleic Acid, 98%	112-80-1	>480	>480	>240
Oleum (20% Free SO <sub>3</sub> )	8014-95-7	239	141	NT
Olive Oil	8001-25-0	NT	NT	NT
Oxalic Acid, Saturated, >10%	144-62-7	> 480	> 480	>240
Oxalic Acid (s), 99%	144-62-7	> 480	> 480	>240
Paraffin Oil	8012-95-1	> 480	> 480	>240
Pentachloropropane	23153-23-3	NT	NT	NT
Pentane	109-66-0	112	108	NT
Peracetic acid solution, 39%	79-21-0	NT	NT	NT
Perchloric Acid, 70%	7601-90-3	>480	>480	>240
Petroleum Benzine	64742-49-0	NT	NT	NT
Petroleum Ether	68476-50-6	NT	NT	NT
Phenol (s), ~100%	108-95-2	>480	>480	>240
Phenol, > 89%	108-95-2	>480	>480	>240
Phenol, 10%	108-95-2	>480	>480	>240
Phosphoric Acid, 5%	7664-38-2	> 480	> 480	> 240
Phosphoric Acid, 10%	7664-38-2	> 480	> 480	> 240
Phosphoric Acid, 15%	7664-38-2	> 480	> 480	> 240
Phosphoric Acid, 20%	7664-38-2	> 480	> 480	> 240

**Showa N8 Permeation Data**

Chemical	CAS Number	TTL	TTL	INT
		ASTM F739	EN 374	ASTM F1383
		BT	BT	BT
		(minutes)	(minutes)	(minutes)
Phosphoric Acid, 25%	7664-38-2	> 480	> 480	>240
Phosphoric Acid, 30%	7664-38-2	> 480	> 480	>240
Phosphoric Acid, 35%	7664-38-2	> 480	> 480	>240
Phosphoric Acid, 40%	7664-38-2	> 480	> 480	>240
Phosphoric Acid, 45%	7664-38-2	> 480	> 480	>240
Phosphoric Acid, 50%	7664-38-2	> 480	> 480	> 240
Phosphoric Acid, 55%	7664-38-2	> 480	> 480	>240
Phosphoric Acid, 60%	7664-38-2	> 480	> 480	>240
Phosphoric Acid, 65%	7664-38-2	> 480	> 480	>240
Phosphoric Acid, 70%	7664-38-2	> 480	> 480	>240
Phosphoric Acid, 75%	7664-38-2	> 480	> 480	>240
Phosphoric Acid, 80%	7664-38-2	> 480	> 480	>240
Phosphoric Acid, 85%	7664-38-2	> 480	> 480	> 240
Phosphoric Acid (s), 99%	7664-38-2	> 480	> 480	>240
Polyethylene Glycol (s), > 98%	25322-68-3	>480	>480	>240
Polyethylene Glycol, Saturated (> 67 %)	25322-68-3	>480	>480	>240
Potassium Bicarbonate (s), > 99%	298-14-6	>480	>480	>240
Potassium Bicarbonate, Saturated (> 36%)	298-14-6	>480	>480	>240
Potassium Bisulfite (s), > 95%	7773-03-7	>480	>480	>240
Potassium Bisulfite, Saturated (> 49%)	7773-03-7	>480	>480	>240
Potassium Carbonate (s), >98%	584-08-7	>480	>480	>240
Potassium Carbonate, Saturated (> 138%)	584-08-7	>480	>480	>240
Potassium Chloride (s), 99%	7447-40-7	> 480	> 480	> 240
Potassium Chloride, Saturated (> 35%)	7447-40-7	>480	>480	>240
Potassium Hydroxide (s), 99%	1310-58-3	> 480	> 480	> 240
Potassium Hydroxide, 5%	1310-58-3	>480	>480	>240
Potassium Hydroxide, 10%	1310-58-3	> 480	> 480	> 240
Potassium Hydroxide, 15%	1310-58-3	>480	>480	>240

**Showa N8 Permeation Data**

Chemical	CAS Number	TTL	TTL	INT
		ASTM F739	EN 374	ASTM F1383
		BT	BT	BT
		(minutes)	(minutes)	(minutes)
Potassium Hydroxide, 20%	1310-58-3	> 480	> 480	> 240
Potassium Hydroxide, 25%	1310-58-3	>480	>480	>240
Potassium Hydroxide, 30%	1310-58-3	> 480	> 480	> 240
Potassium Hydroxide, 35%	1310-58-3	>480	>480	>240
Potassium Hydroxide, 40%	1310-58-3	>480	>480	>240
Potassium Hydroxide, 45%	1310-58-3	> 480	> 480	>240
Potassium Hydroxide, 50%	1310-58-3	>480	>480	>240
Potassium Hydroxide, 54%	1310-58-3	>480	>480	>240
Potassium Permanganate (s), > 99%	7722-64-7	>480	>480	>240
Potassium Permanganate, Saturated (> 76%)	7722-64-7	>480	>480	>240
Propanediamine, N,N'-Dimethyl	109-55-7	NT	NT	NT
Propanol, 1-	71-23-8	> 480	> 480	> 240
Propyl Acetate	109-60-4	NT	NT	NT
Propylene Glycol	57-55-6	> 480	> 480	> 240
Propylene Glycol Monobutyl Ether	5131-66-8	NT	NT	NT
Propylene Glycol Monomethyl Ether	107-98-2	NT	NT	NT
Propylene Glycol Monomethyl Ether Acetate	108-65-6	NT	NT	NT
Propylene Glycol Monopropyl Ether	1569-01-3	NT	NT	NT
Propylene Oxide	75-56-9	NT	NT	NT
Pyridine	110-86-1	NT	NT	NT
Quartz (s), 99%	14808-60-7	>480	>480	>240
Salicylic acid (s), 99%	69-72-7	> 480	> 480	> 240
Screen Wash Universal (ZT639)	mixture	NT	NT	NT
Selenium Sulfide (s), 99%	7488-56-4	>480	>480	>240
Skydrol 500B-4	mixture	>480	>480	>240
Skydrol LD-4	mixture	>480	>480	>240
Silicon Dioxide (s), 99%	7631-86-9	>480	>480	>240
Sodium Bicarbonate (s), 99%	144-55-8	> 480	> 480	> 240
Sodium Bicarbonate, Saturated (> 10%)	144-55-8	>480	>480	>240

**Showa N8 Permeation Data**

Chemical	CAS Number	TTL	TTL	INT
		ASTM F739	EN 374	ASTM F1383
		BT	BT	BT
		(minutes)	(minutes)	(minutes)
Sodium Bisulfite (s), > 95%	7631-90-5	> 480	> 480	>240
Sodium Bisulfite, Saturated (> 42%)	7631-90-5	> 480	> 480	>240
Sodium Tetraborate Decahydrate (s), > 99%	1303-96-4	> 480	> 480	>240
Sodium Tetraborate Decahydrate, Saturated (> 49%)	1303-96-4	> 480	> 480	>240
Sodium Carbonate (s), 99%	497-19-8	> 480	> 480	>240
Sodium Carbonate, Saturated (> 9%)	497-19-8	> 480	> 480	>240
Sodium Chloride (s), 99%	7647-14-5	> 480	> 480	> 240
Sodium Chloride, Saturated (> 36%)	7647-14-5	> 480	> 480	>240
Sodium Lauryl Sulfate (s), > 90%	151-21-3	> 480	> 480	>240
Sodium Lauryl Sulfate, Saturated (> 15%)	151-21-3	> 480	> 480	>240
Sodium Fluoride (s), > 99%	7681-49-4	> 480	> 480	>240
Sodium Fluoride, Saturated (> 4%)	7681-49-4	> 480	> 480	>240
Sodium Gluconate (s), > 98%	527-07-1	> 480	> 480	>240
Sodium Gluconate, Saturated (> 59%)	527-07-1	> 480	> 480	>240
Sodium Hydroxide (s), 98%	1310-73-2	>480	>480	>240
Sodium Hydroxide, 5%	1310-73-2	>480	>480	>240
Sodium Hydroxide, 10%	1310-73-2	>480	>480	>240
Sodium Hydroxide, 15%	1310-73-2	>480	>480	>240
Sodium Hydroxide, 20%	1310-73-2	>480	>480	>240
Sodium Hydroxide, 25%	1310-73-2	>480	>480	>240
Sodium Hydroxide, 30%	1310-73-2	>480	>480	>240
Sodium Hydroxide, 35%	1310-73-2	>480	>480	>240
Sodium Hydroxide, 40%	1310-73-2	>480	>480	>240
Sodium Hydroxide, 45%	1310-73-2	>480	>480	>240
Sodium Hydroxide, 50%	1310-73-2	>480	>480	>240
Sodium Hypochlorite, 12%	7681-52-9	>480	>480	>240
Sodium Hypochlorite, 6%	7681-52-9	>480	>480	>240
Sodium Metabisulfite (s), > 97%	7681-57-4	>480	>480	>240
Sodium Metasilicate (s), > 98%	6834-92-0	>480	>480	>240

**Showa N8 Permeation Data**

Chemical	CAS Number	TTL	TTL	INT
		ASTM F739	EN 374	ASTM F1383
		BT	BT	BT
		(minutes)	(minutes)	(minutes)
Sodium Metasilicate, Saturated (> 21%)	6834-92-0	>480	>480	>240
Sodium Nitrite (s), > 97%	7632-00-0	>480	>480	>240
Sodium Nitrite, Saturated (> 82%)	7632-00-0	>480	>480	>240
Sodium Permanganate (s), > 95%	10101-50-5	>480	>480	>240
Sodium Permanganate Solution, 40%	10101-50-5	>480	>480	>240
Sodium Selenite (s), > 98%	10102-18-8	>480	>480	>240
Sodium Selenite, Saturated (> 89%)	10102-18-8	>480	>480	>240
Sodium Sulfate (s), > 99%	7757-82-6	>480	>480	>240
Sodium Sulfate, Saturated (> 28%)	7757-82-6	>480	>480	>240
Sodium Sulfite (s), > 98%	7757-83-7	>480	>480	>240
Sodium Sulfite, Saturated (> 27%)	7757-83-7	>480	>480	>240
Sodium Thiosulfate (s), > 98%	7772-98-7	>480	>480	>240
Sodium Thiosulfate, Saturated (> 70%)	7772-98-7	>480	>480	>240
Soybean oil	8001-22-7	NT	NT	NT
Stoddard Solvent	8052-41-3	NT	NT	NT
Styrene	100-42-5	NT	NT	NT
Sulfuric Acid, 10%	7664-93-9	> 480	> 480	> 240
Sulfuric Acid, 15%	7664-93-9	> 480	> 480	>240
Sulfuric Acid, 18%	7664-93-9	> 480	> 480	>240
Sulfuric Acid, 25%	7664-93-9	> 480	> 480	> 240
Sulfuric Acid, 30%	7664-93-9	> 480	> 480	>240
Sulfuric Acid, 39%	7664-93-9	> 480	> 480	>240
Sulfuric Acid, 47%	7664-93-9	> 480	> 480	> 240
Sulfuric Acid, 50%	7664-93-9	> 480	> 480	> 240
Sulfuric Acid, 70%	7664-93-9	> 480	> 480	> 240
Sulfuric Acid, 93%	7664-93-9	314	279	> 240
Sulfuric Acid, 96%	7664-93-9	314	279	> 240
Talc (s), >99%	14807-96-6	>480	>480	> 240
Tannic Acid (s), 95%	1401-55-4	>480	>480	> 240



**Showa N8 Permeation Data**

Chemical	CAS Number	TTL	TTL	INT
		ASTM F739	EN 374	ASTM F1383
		BT	BT	BT
		(minutes)	(minutes)	(minutes)
Tetrachloroethylene	127-18-4	39	39	NT
Tetrachloropropene	10436-39-2	60	53	NT
Tetrahydrofuran	109-99-9	NT	NT	NT
Tetramethylammonium Hydroxide, 25%	75-59-2	>480	>480	>240
Titanium Dioxide (s), > 99%	13463-67-7	> 480	> 480	> 240
Toluene	108-88-3	19	18	26
Toluene-2,4-diisocyanate	584-84-9	>480	>480	>240
Toluene-2,6-diisocyanate	91-08-7	NT	NT	NT
Toluidine, O-	95-53-4	NT	NT	NT
Tricalcium Phosphate (s), > 95%	7758-87-4	> 480	> 480	> 240
Trichlorobenzene, 1,2,4-	120-82-1	NT	NT	NT
Trichloroethylene	79-01-6	12	12	NT
Tricresyl Phosphate	1330-78-5	NT	NT	NT
Triethanolamine	102-71-6	NT	NT	NT
Triethylamine	121-44-8	NT	NT	NT
Triethylene Glycol Monobutyl Ether	143-22-6	NT	NT	NT
Triethylene Glycol Monoethyl Ether	112-50-5	NT	NT	NT
Triethylene Glycol Monomethyl Ether	112-35-6	NT	NT	NT
Trimethyl Phosphate	512-56-1	NT	NT	NT
Trimethylbenzene	95-63-6	NT	NT	NT
Turpentine	8006-64-2	NT	NT	NT
Urea Solution, 30 to 35%	57-13-6	>480	>480	>240
Urea, Saturated Solution, >62%	57-13-6	>480	>480	>240
Urea (s), 99%	57-13-6	>480	>480	>240
Vinyl Acetate	108-05-4	NT	NT	NT
Vinyl Pyrrolidinone	88-12-0	NT	NT	NT
VM&P Naphtha	8030-30-6	236	300	NT
Xylene	1330-20-7	26	27	35
Zinc (s), >98%	7440-66-6	> 480	> 480	> 240
Zinc Oxide (s), >99%	1314-13-2	> 480	> 480	> 240





**Showa N8 Permeation Data**

Chemical	CAS Number	TTL	TTL	INT
		ASTM F739	EN 374	ASTM F1383
		BT	BT	BT
		(minutes)	(minutes)	(minutes)
Zinc Sulfate, Heptahydrate (s), > 99%	7446-20-0	>480	>480	>240
Zinc Sulfate, Saturated (> 96%)	7446-20-0	>480	>480	>240
Zinc Sulfate, Monohydrate (s), > 99%	7446-19-7	>480	>480	>240
Zinc Sulfate, Saturated (> 35%)	7446-19-7	>480	>480	>240

Permeation is the act of a chemical passing through a solid material, such as personal protective clothing, on a molecular level.

TTL : Total immersion chemical permeation breakthrough time (maximum test duration of 480 minutes).

INT : Intermittent contact chemical permeation breakthrough time, one minute immersion out of every ten minutes repeatedly, up to maximum test duration of 240 minutes.

The information provided in this chart is intended to help you determine the general suitability of SHOWA gloves in the end-user’s particular application. It is the responsibility of the purchaser and/or user to determine the level of toxicity of the materials to be handled and to select the proper glove suitable for a particular application. The information provided reflects laboratory performance of gloves under carefully controlled conditions. SHOWA makes no guarantee of results and assumes no obligation or liability in connection with this information.