

Chemical Compatibility Guide for: SHOWA KV660 PVC Coated Cut-Resistant Gloves

The guide on the following page(s) was provided by the supplier.
New Pig Corporation assumes no responsibility, obligation, or
liability in conjunction with the use or misuse of the information.



New Pig

One Pork Avenue
Tipton, PA 16684-0304

newpig.com

North America: **1-800-468-4647**

Europe: **+31 (0)76 596 92 50**

China: **+86-21-400 921 5178**

PIG, PIG logo are registered trademarks in USA and other countries. See tm.newpig.com


UK: **0800 919 900**

Outside North America: **+1-814-684-0101**



SHOWA ATLAS KV660

Material PVC LENGTH 12 in. / 300mm



CHEMICAL PERMEATION

CHEMICAL NAME	CAS NUMBER	BDT	
		TTL ASTM F739	INT ASTM F1383
Carbon Tet	56-23-5	>30	NT
Urea (s) 62%	57-13-6	>480	>240
Urea (s) 99%	57-13-6	>480	>240
Urea (s) 35%	57-13-6	>480	>240
1,2-Propanediol	57-55-6	480	NT
Diethyl Ether	60-29-7	1-5	NT
Aminobenzene	62-53-3	>30	NT
Ethanol	64-17-5	>30	NT
Acetic Acid 99%	64-19-7	>60	NT
Acetic Acid 84%	64-19-7	>120	NT
Acetic Acid 50%	64-19-7	>120	NT
Acetic Acid 10%	64-19-7	>480	>240
Benzoic Acid (s) 99%	65-85-0	>480	>240
Methanol	67-56-1	>10	NT
2-Propanol	67-63-0	>60	NT
2-Propanone	67-64-1	NT	>10
Chloroform	67-66-3	NT	>10
Dimethylsulfoxide (DMSO)	67-68-5	>240	>240
Dimethyl Formamide	68-12-2	>30	NT
Salicylic acid (s) 99%	69-72-7	>480	>240
n-Propanol	71-23-8	>120	NT
Butanol	71-36-3	NT	>240
Alcohol, Amyl	71-41-0	>480	>240
Benzene	71-43-2	>10	>10

1,1,1-Trichloroethane	71-55-6	>10	NT
Chloride, Methyl (GAS)	74-87-3	>10	NT
Acetonitrile	75-05-8	>10	NT
Acetaldehyde	75-07-0	6-10	NT
Chloride, Methylene	75-09-2	1-5	NT
Bromoform	75-25-2	>10	NT
Nitromethane	75-52-5	>10	NT
1,2-Epoxypropane	75-56-9	6-10	NT
1,1,2-Trichloro-1,2,2-trifluoroethane	76-13-1	>10	NT
Citric Acid 30%	77-92-9	480	NT
Citric Acid 50%	77-92-9	>480	>240
Citric Acid 99%	77-92-9	>480	>240
Citric Acid 75%	77-92-9	>480	>240
2-Butanol	78-83-1	NT	>240
2-Butanone	78-93-3	>10	NT
Ethylene, Trichloride	79-01-6	6-10	NT
2-Propeneamide 50%	79-06-1	>480	>240
2-Propeneamide(s) 99%	79-06-1	480	NT
2-Propeneamide 98%	79-06-1	>480	>240
Chloroacetic Acid 70%	79-11-8	480	NT
Acetate, Methyl	79-20-9	1-5	NT
Methacrylic Acid 99%	79-41-4	>60	NT
DBP	84-74-2	>240	NT
Vinyl Pyrrolidinone	88-12-0	>120	NT
1,2,4 - Trimethyl Benzene 98%	95-63-6	>10	NT
Butanone Oxime	96-29-7	1-5	NT
2-Furaldehyde	98-01-1	>10	NT
Benzene, Trifluoromethyl	98-08-8	>10	NT
Butyl Toluene, p-Tert	98-51-1	480	NT
1-chloro-4-[trifluoromethyl]Benzene	98-56-6	>10	NT
(1-Methylethyl)benzene	98-82-8	6-10	NT
1-Phenylethanone	98-86-2	>60	NT
Benzene, Ethyl	100-41-4	>10	NT
Benzene, Vinyl	100-42-5	>10	NT
Benzaldehyde	100-52-7	>60	NT
2,2',2''-Nitrilotriethanol	102-71-6	480	NT
±-2-(Chloromethyl)oxiran	106-89-8	>10	NT

1,2-Dichloroethane	107-06-2	NT	>10
Acrylonitrile	107-13-1	6-10	NT
2-Propen-1-ol	107-18-6	>30	NT
1,2-Ethanediol	107-21-1	>480	NT
Methyl Propyl Ketone	107-87-9	NT	>10
1-methoxy-2-propanol	107-98-2	>60	NT
Acetate, Vinyl	108-05-4	1-5	NT
Acetate, Isopropyl	108-21-4	6-10	NT
2,6-Dimethyl-4-Heptanone	108-83-8	>60	NT
Benzene, Methyl	108-88-3	NT	>10
Cyclohexanol	108-93-0	NT	>240
Cyclohexanone	108-94-1	>60	NT
Carbolic Acid 89%	108-95-2	>480	>240
Dimethyl Propanamide, N,N'	109-55-7	>10	NT
Pentane	109-66-0	>10	NT
1-Aminobutane	109-73-9	6-10	NT
DEA	109-89-7	6-10	NT
Diethylene Oxide	109-99-9	>10	NT
Hexane	110-54-3	>10	NT
Cyclohexane	110-82-7	>120	NT
Diethylene oximide	110-91-8	>30	NT
n-Octane	111-65-9	>60	NT
2-Butoxyethanol	111-76-2	>60	NT
Oleic Acid 98%	112-80-1	>480	NT
3-Methyl-1-butanol	123-51-3	>10	NT
Butyl Acetate	123-86-4	>30	NT
1,4-Dioxane	123-91-1	>10	NT
PERC	127-18-4	>10	NT
Dimethylacetamide N,N-	127-19-5	>10	NT
Butyl Acrylate	141-32-2	>30	NT
2-Aminoethanol	141-43-5	>480	NT
Ethyl Acetate	141-78-6	6-10	NT
Heptane	142-82-5	>60	NT
3,4-DCBTF	328-84-7	>30	NT
Calcium Carbonate (s) 99%	471-34-1	>480	>240
2,2,4-Trimethyl Pentane	540-84-1	NT	>240
3-Methyl-2-Butanone	563-80-4	>10	NT

Amyl Acetate	628-63-7	>60	NT
Methyl Pyrrolidone, N-	872-50-4	>60	NT
2-Bromoethyl Acetate	927-68-4	>30	NT
3,8-Diamino-5-ethyl-6-phenylphenanthridinium bromide 95%	1239-45-8	>480	>240
3,8-Diamino-5-ethyl-6-phenylphenanthridinium bromide 5%	1239-45-8	>480	>240
3,8-Diamino-5-ethyl-6-phenylphenanthridinium bromide 1%	1239-45-8	>480	>240
3,8-Diamino-5-ethyl-6-phenylphenanthridinium bromide 10%	1239-45-8	>480	>240
Calcium Hydroxide (s) 95%	1305-62-0	>480	>240
Iron Oxide (s) 99%	1309-37-1	>480	>240
Caustic Potash 20%	1310-58-3	>480	>240
Caustic Potash 10%	1310-58-3	>480	>240
Caustic Potash 30%	1310-58-3	>480	>240
Caustic Potash 99%	1310-58-3	>480	>240
Caustic Soda 40%	1310-73-2	NT	>240
Caustic Soda 98%	1310-73-2	>480	>240
Caustic Soda 20%	1310-73-2	>480	>240
Caustic Soda 30%	1310-73-2	>480	>240
Caustic Soda 10%	1310-73-2	>480	>240
Caustic Soda 50%	1310-73-2	NT	>240
Divinyl Benzene	1321-74-0	6-10	NT
dimethyl benzene	1330-20-7	>10	NT
Tricresyl Phosphate	1330-78-5	480	NT
Ammonia Solution 29%	1336-21-6	>30	NT
1-Propoxy-2-propanol	1569-01-3	>30	NT
Methyl-Tert-Butyl Ether	1634-04-4	>10	NT
Butoxypropanol	5131-66-8	>120	NT
D-Limonene	5989-27-5	>30	NT
Aluminum Chloride (s) 98%	7446-70-0	>480	>240
Potassium Chloride (s) 99%	7447-40-7	>480	>240
Hydrochloric Acid 10%	7647-01-0	NT	>240
Hydrochloric Acid 37%	7647-01-0	NT	>240
Muriatic Acid 20%	7647-01-0	NT	>240
Muriatic Acid 32%	7647-01-0	NT	>240
Phosphoric Acid 10%	7664-38-2	>480	>240
Phosphoric Acid 50%	7664-38-2	>480	>240
Hydrofluoric Acid 40%	7664-39-3	NT	>240
Hydrofluoric Acid 48%	7664-39-3	>60	NT

Battery Acid 70%	7664-93-9	NT	>240
Battery Acid 10%	7664-93-9	NT	>240
Battery Acid 25%	7664-93-9	NT	>240
Battery Acid 50%	7664-93-9	NT	>240
Battery Acid 47%	7664-93-9	NT	>240
Bleach: Sodium Hypochlorite 12%	7681-52-9	>480	>240
Bleach: Sodium Hypochlorite 6%	7681-52-9	>480	>240
Nitric Acid 23%	7697-37-2	NT	>240
Nitric Acid 35%	7697-37-2	480	>240
Nitric Acid 50%	7697-37-2	NT	>240
Nitric Acid 70%	7697-37-2	>60	NT
Nitric Acid 10%	7697-37-2	NT	>240
Hydrogen Peroxide 30%	7722-84-1	480	NT
Iron Chloride Solution 45%	7758-94-3	>480	>240
Iron Chloride Solution 98%	7758-94-3	>480	>240
Chlorine (Gas)	7782-50-5	>30	NT
Iron Sulfate (s) 99%	7782-63-0	>480	>240
Hydroxylamine 50%	7803-49-8	NT	NT
Gasoline (unleaded)	8006-61-9	>30	NT
Fir Oil	8006-64-2	>120	NT
Ligroin	8032-32-4	>120	NT
Dry Cleaning Mineral Spirits	8052-41-3	>120	NT
Hydrobromic Acid 48%	10035-10-6	>480	>240
Boric acid (s) 99%	10043-35-3	>480	>240
Calcium Chloride (s) 96%	10043-52-4	>480	>240
Tetrachloropropene	10436-39-2	>30	NT
Ammonium Fluoride 40%	12125-01-8	NT	NT
Talc (s)	14807-96-6	>480	>240
1-Chloro-2-Methyl Benzene	25168-05-2	>10	NT
Dry cleaning safety solvent	64475-85-0	>60	NT
Mineral Spirits (White Spirits Type 0)	64742-88-7	NT	>240
Diesel Fuel	77650-28-3	NT	>240

BDT=BREAKTHROUGH DETECTION TIME

THE LEVEL (0 TO 6) INDICATES THE TIME REQUIRED FOR DIFFERENT CHEMICALS TO PERMEATE THROUGH THE GLOVE.

TTL : TOTAL IMMERSION CHEMICAL PERMEATION BREAKTHROUGH TIME.

INT : INTERMITTENT CONTACT CHEMICAL PERMEATION BREAKTHROUGH TIME, ONE MINUTE IMMERSION OUT OF EVERY TEN, REPEATEDLY.

Warranty Limitations and Disclaimer Use

This information is provided solely as a convenience to help you evaluate our gloves in the end-user's particular application. It is the responsibility of the purchaser and/or user to determine the level of toxicity of the materials to be handled and to select the proper glove suitable for a particular application. The information provided reflects laboratory performance of gloves under carefully controlled conditions. SHOWA makes no guarantee of results and assumes no obligation or liability in connection with this information.

