

Chemical Compatibility Guide for: SHOWA Atlas 460 PVC Gloves

The guide on the following page(s) was provided by the supplier. New Pig Corporation assumes no responsibility, obligation, or liability in conjunction with the use or misuse of the information.



New Pig

One Pork Avenue
Tipton, PA 16684-0304

newpig.com

North America: **1-800-468-4647**

Europe: **+31 (0)76 596 92 50**

China: **+86-21-400 921 5178**

PIG, PIG logo are registered trademarks in USA and other countries. See tm.newpig.com


UK: **0800 919 900**

Outside North America: **+1-814-684-0101**



ATLAS 460

Material PVC LENGTH 12 in. / 300mm



CHEMICAL PERMEATION

CHEMICAL NAME	CAS NUMBER	BDT	
		TTL ASTM F739	INT ASTM F1383
Carbon Tet	56-23-5	>30	NT
Urea (s) 35%	57-13-6	>480	>240
Urea (s) 62%	57-13-6	>480	>240
Urea (s) 99%	57-13-6	>480	>240
Aminobenzene	62-53-3	>60	NT
Acetic Acid 10%	64-19-7	>480	>240
Benzoic Acid (s) 99%	65-85-0	>480	>240
2-Propanol	67-63-0	>30	NT
2-Propanone	67-64-1	NT	6-10
Chloroform	67-66-3	NT	6-10
Dimethylsulfoxide (DMSO)	67-68-5	>120	NT
Salicylic acid (s) 99%	69-72-7	>480	>240
n-Propanol	71-23-8	>60	NT
Benzene	71-43-2	6-10	NT
Acetonitrile	75-05-8	>10	NT
Chloride, Methylene	75-09-2	1-5	NT
Tetramethylammonium Hydroxide 25%	75-59-2	480	NT
Citric Acid 30%	77-92-9	>480	>240
Citric Acid 50%	77-92-9	>480	>240
Citric Acid 75%	77-92-9	>480	>240
Citric Acid 99%	77-92-9	>480	>240
2-Butanone	78-93-3	1-5	NT
2-Propenamide 98%	79-06-1	>480	>240
2-Propenamide 50%	79-06-1	>480	>240
Methacrylic Acid 99%	79-41-4	>60	NT
Benzene, Ethyl	100-41-4	6-10	NT

1,2-Dichloroethane	107-06-2	NT	6-10
Acrylonitrile	107-13-1	1-5	NT
Methyl Propyl Ketone	107-87-9	NT	6-10
2-Pentanone, Methyl-	108-10-1	NT	>10
Benzene, Methyl	108-88-3	NT	>10
Cyclohexanone	108-94-1	>30	NT
Carbolic Acid 89%	108-95-2	NT	>60
Pentane	109-66-0	>10	NT
Hexane	110-54-3	>10	NT
n-Octane	111-65-9	>30	NT
2-Butoxyethanol	111-76-2	>60	NT
Dimethylamine 40%	124-40-3	>60	NT
PERC	127-18-4	>10	NT
Ethyl Acetate	141-78-6	6-10	NT
Heptane	142-82-5	>10	NT
Calcium Carbonate (s) 99%	471-34-1	>480	>240
3-Methyl-2-Butanone	563-80-4	6-10	NT
3,8-Diamino-5-ethyl-6-phenylphenanthridinium bromide 1%	1239-45-8	>480	>240
3,8-Diamino-5-ethyl-6-phenylphenanthridinium bromide 10%	1239-45-8	>480	>240
3,8-Diamino-5-ethyl-6-phenylphenanthridinium bromide 95%	1239-45-8	>480	>240
3,8-Diamino-5-ethyl-6-phenylphenanthridinium bromide 5%	1239-45-8	>480	>240
Calcium Hydroxide (s) 95%	1305-62-0	>480	>240
Iron Oxide (s) 99%	1309-37-1	>480	>240
Caustic Potash 30%	1310-58-3	>480	>240
Caustic Potash 20%	1310-58-3	>480	>240
Caustic Soda 50%	1310-73-2	480	NT
Caustic Soda 40%	1310-73-2	480	NT
Caustic Soda 20%	1310-73-2	>480	>240
Caustic Soda 30%	1310-73-2	>480	>240
Caustic Soda 10%	1310-73-2	480	>120
Caustic Soda 98%	1310-73-2	480	>120
Chromic Acid Solution 99%	1333-82-0	>480	>240
Ammonia Solution 29%	1336-21-6	>10	NT
Butoxypropanol	5131-66-8	>60	NT
Aluminum Chloride (s) 98%	7446-70-0	>480	>240
Potassium Chloride (s) 99%	7447-40-7	>480	>240
Sodium Chloride (s) 99%	7647-14-5	>480	>240

Phosphoric Acid 85%	7664-38-2	>480	>240
Phosphoric Acid 10%	7664-38-2	>480	>240
Phosphoric Acid 50%	7664-38-2	>480	>240
Hydrofluoric Acid 99%	7664-39-3	1-5	NT
Hydrofluoric Acid 48%	7664-39-3	>120	NT
Battery Acid 96%	7664-93-9	>120	NT
Bleach: Sodium Hypochlorite 6%	7681-52-9	>480	>240
Bleach: Sodium Hypochlorite 12%	7681-52-9	>480	>240
Nitric Acid 35%	7697-37-2	>240	>120
Nitric Acid 65%	7697-37-2	>60	NT
Iron Chloride Solution 45%	7758-94-3	>480	>240
Iron Chloride Solution 98%	7758-94-3	>480	>240
Chlorine (Gas)	7782-50-5	>10	NT
Iron Sulfate (s) 99%	7782-63-0	>480	>240
Hydroxylamine 50%	7803-49-8	480	NT
Hydrobromic Acid 48%	10035-10-6	>480	>240
Boric acid (s) 99%	10043-35-3	>480	>240
Calcium Chloride (s) 96%	10043-52-4	>480	>240
Ammonium Fluoride 40%	12125-01-8	480	NT
Talc (s) 99%	14807-96-6	>480	>240
Pentachloropropane	23153-23-3	>30	NT
Antimony Tributylate 95%	53856-17-0	>480	>240
Kerosene (hydrosulfurized)	64742-81-0	>480	>240
Mineral Spirits (White Spirits Type 0)	64742-88-7	>240	>240

BDT=BREAKTHROUGH DETECTION TIME

THE LEVEL (0 TO 6) INDICATES THE TIME REQUIRED FOR DIFFERENT CHEMICALS TO PERMEATE THROUGH THE GLOVE.

TTL : TOTAL IMMERSION CHEMICAL PERMEATION BREAKTHROUGH TIME.

INT : INTERMITTENT CONTACT CHEMICAL PERMEATION BREAKTHROUGH TIME, ONE MINUTE IMMERSION OUT OF EVERY TEN, REPEATEDLY.

Warranty Limitations and Disclaimer Use

This information is provided solely as a convenience to help you evaluate our gloves in the end-user's particular application. It is the responsibility of the purchaser and/or user to determine the level of toxicity of the materials to be handled and to select the proper glove suitable for a particular application. The information provided reflects laboratory performance of gloves under carefully controlled conditions. SHOWA makes no guarantee of results and assumes no obligation or liability in connection with this information.