

Chemical Compatibility Guide for: PIG DrainBlocker Drain Cover

This report is offered as a guide and was developed from information which, to the best of New Pig's knowledge, was reliable and accurate. Due to variables and conditions of application beyond New Pig's control, none of the data shown in this guide is to be construed as a guarantee, expressed or implied. New Pig assumes no responsibility, obligation, or liability in conjunction with the use or misuse of the information.



New Pig

One Pork Avenue
Tipton, PA 16684-0304

newpig.com

North America: **1-800-468-4647**

Europe: **+31 (0)76 596 92 50**

China: **+86-21-400 921 5178**

PIG, PIG logo are registered trademarks in USA and other countries. See tm.newpig.com

UK: **0800 919 900**

Outside North America: **+1-814-684-0101**

Chemical Compatibility Guide

Guide Applicable to the Following:

PIG DrainBlocker Drain Cover

Guide Information:

This report is offered as a guide and was developed from information which, to the best of New Pig's knowledge, was reliable and accurate. Due to variables and conditions of application beyond New Pig's control, none of the data shown in this guide is to be construed as a guarantee, expressed or implied. New Pig assumes no responsibility, obligation, or liability in conjunction with the use or misuse of the information.

Tests were run per New Pig Corporation Test Procedure #0002, *except those marked with an asterisk which were run using New Pig Test Procedure #0003.

All tests exposed each chemical to a drain cover for a minimum of four hours.

Ratings/Key of Ratings – Chemical Effect

Degradation — Any physical change in the material: Swelling, discoloration, delamination, curling, etc.

Degradation Rating — 0 = None; 1 = Slight; 2 = Significant

Seal — Any change to the seal between the blocker and the sealing surface

Seal Rating — 0 = None; 1 = Slight; 2 = Significant

Overall Compatability — The material's ability to resist chemical degradation and maintain a seal

Overall Compatability Rating — Good = Can withstand 4 or more hours of chemical exposure

Fair = Can withstand 2–4 hours of chemical exposure

(ER) Emergency Response = Can withstand 30 min. to 2 hours of chemical exposure

(NR) Not Recommended = Not recommended for use with this chemical

Note: Blocker products that have been chemically degraded may be considered hazardous waste because of their mixture with a hazardous liquid.

Dispose of in accordance with Federal, State and Local requirements.

Chemical Name	Chemical Class	Degradation Rating	Seal Rating	Overall Compatability Rating	Comments
Acetone	Ketone	2	0	Good	Significant Degradation of the top layer only. No effect on Urethane layer.
Chlorine Standard Solution (1000ppm)	Halogen	0	0	Good	
Ethanol (95%)	alcohol	0	0	Good	
Hydraulic Fluid	Aliphatic Hydrocarbon	0	0	Good	
Hydrochloric Acid (18.5%)	Inorganic Acid	0	0	Fair	
Hydrogen Peroxide (30%)	Peroxide	0	1	Fair	Urethane had blistering after 2 hours
Isopropyl Alcohol	Hydroxylic Compound	0	0	Good	
Mineral Oil	Petroleum Hydrocarbon	0	0	Good	
"Chlorine Bleach (5% Sodium Hypochlorite)"	Inorganic Halogen	1	0	Good	
Sodium Hydroxide (40%)	Inorganic Base	0	0	Good	
Sulfuric Acid (50%)	Inorganic Acid	1	1	Fair	Urethane began to breakdown after 2 hours
Xylene	Aromatic Hydrocarbon	1	1	Fair	Urethane began to swell after 6 hours
Gasoline	Petroleum Hydrocarbon	0	0	Good	
Antifreeze	Glycol Ether	0	0	Good	
Diesel Fuel	Petroleum Hydrocarbon	0	0	Good	