

Chemical Compatibility Guide for: PIG Collapse-A-Tainer with XR-5[®]

The guide on the following page(s) was provided by the supplier.
New Pig Corporation assumes no responsibility, obligation, or
liability in conjunction with the use or misuse of the information.



New Pig

One Pork Avenue
Tipton, PA 16684-0304

newpig.com

North America: **1-800-468-4647**

Europe: **+31 (0)76 596 92 50**

PIG, PIG logo are registered trademarks in USA and other countries. See tm.newpig.com

UK: **0800 919 900**

Outside North America: **+1-814-684-0101**

330282

Last revised 1/28/2014

Section 3 - Chemical/Environmental Resistance

Part 1 - XR-5® Fluid Resistance Guidelines

The data below is the result of laboratory tests and is intended to serve only as a guide. No performance warranty is intended or implied. The degree of chemical attack on any material is governed by the conditions under which it is exposed. Exposure time, temperature, and size of the area of exposure usually varies considerably in application, therefore, this table is given and accepted at the user's risk. Confirmation of the validity and suitability in specific cases should be obtained.

When considering XR-5 for specific applications, it is suggested that a sample be tested in actual service before specification. Where impractical, tests should be devised which simulate actual service conditions as closely as possible.

EXPOSURE	RATING	EXPOSURE	RATING
AFFF	A	JP-4 Jet Fuel	A
Acetic Acid (5%)	B	JP-5 Jet Fuel	A
Acetic Acid (50%)	C	JP-8 Jet Fuel	A
Ammonium Phosphate	T	Kerosene	A
Ammonium Sulfate	T	Magnesium Chloride	T
Antifreeze (ethylene glycol)	A	Magnesium Hydroxide	T
Animal Oil	A	Methanol	A
Aqua Regia	X	Methyl Alcohol	A
ASTM Fuel A (100% Iso-octane)	A	Methyl Ethyl Ketone	X
ASTM Oil #2 (Flash pt. 240° C)	A	Mineral Spirits	A
ASTM Oil #3	A	Naphtha	A
Benzene	X	Nitric Acid (5%)	B
Calcium Chloride Solutions	T	Nitric Acid (50%)	C
Calcium Hydroxide	T	Perchloroethylene	C
20% Chlorine Solution	A	Phenol	X
Clorox	A	Phenol Formaldehyde	B
Conc. Ammonium Hydroxide	A	Phosphoric Acid (50%)	A
Corn Oil	A	Phosphoric Acid (100%)	C
Crude Oil	A	Phthalate Plasticizer	C
Diesel Fuel	A	Potassium Chloride	T
Ethanol	A	Potassium Sulphate	T
Ethyl Acetate	C	Raw Linseed Oil	A
Ethyl Alcohol	A	SAE-30 Oil	A
Fertilizer Solution	A	Salt Water (25%)	B
#2 Fuel Oil	A	Sea Water	A
#6 Fuel Oil	A	Sodium Acetate Solutions	T
Furfural	X	Sodium Bisulfite Solution	T
Gasoline	B	Sodium Hydroxide (60%)	A
Glycerin	A	Sodium Phosphate	T
Hydraulic Fluid- Petroleum Based	A	Sulphuric Acid (50%)	A
Hydraulic Fluid- Phosphate Ester Based	C	Tanic Acid (50%)	A
Hydrocarbon Type II (40% Aromatic)	C	Toluene	C
Hydrochloric Acid (50%)	A	Transformer Oil	A
Hydrofluoric Acid (5%)	A	Turpentine	A
Hydrofluoric Acid (50%)	A	Urea Formaldehyde	A
Hydrofluosilicic Acid (30%)	A	UAN	A
Isopropyl Alcohol	T	Vegetable Oil	A
Ivory Soap	A	Water (200°F)	A
Jet A	A	Xylene	X
		Zinc Chloride	T

Ratings are based on visual and physical examination of samples after removal from the test chemical after the samples of Black XR-5 were immersed for 28 days at room temperature. Results represent ability of material to retain its performance properties when in contact with the indicated chemical.

Rating Key:

- A - Fluid has little or no effect
- B - Fluid has minor to moderate effect
- C - Fluid has severe effect
- T - No data - likely to be acceptable
- X - No data - not likely to be acceptable