



October 1, 2010

Mr. Mark Woytowich  
Business Platform Leader  
Foodservice Division  
New Pig Corporation  
One Pork Ave  
Tipton, PA 16684

Dear Mr. Woytowich

The PIG® Grippy Absorbent Walk-on Surface was tested per the ANSI/NFSI B101.1-2009 Test Method for Measuring Wet SCOF of Common Hard-Surface Floor Materials on September 16, 2010 and the average Static Coefficient of Friction (SCOF) was 0.98 which exceeds our minimum acceptable wet SCOF value of a 0.6. Walkways that possess a wet SCOF of 0.6 or greater are defined by the standard as "High-Traction". When used as part of a floor safety program, these high-traction surfaces have been proven to reduce slip and fall claims by as much as 90%.

Please feel free to contact us if you have any questions. Thank you.

Sincerely,

A handwritten signature in blue ink, appearing to read "Russell J. Kendzior", is written over a thick blue horizontal line.

Russell J. Kendzior  
President



September 20, 2010

Mr. Mark Woytowich  
Business Platform Leader  
Foodservice Division  
New Pig Corporation  
One Pork Ave  
Tipton, PA 16684

Dear Mr. Woytowich:

On behalf of the National Floor Safety Institute I would like to thank you for submitting your product for Phase 1 testing. The PIG<sup>®</sup> Grippy<sup>™</sup> Absorbent Walk-on Surface was tested per the ANSI/NFSI B101.1-2009 Test Method for Measuring Wet SCOF of Common Hard-Surface Floor Materials on September 16, 2010 and the average Static Coefficient of Friction (SCOF) was 0.98 which exceeds our minimum acceptable wet SCOF value of a 0.6 and is therefore eligible for Phase 2 testing.

The purpose of the ANSI/NFSI B101.1-2009 is to determine the wet Static Coefficient Of Friction (SCOF) of hard surfaced flooring materials using the BOT-3000. The product was tested per Phase 1 of our certification process and does not reflect real-world performance as evaluated in Phase 2 testing.

Please feel free to contact us if you have any questions. Thank you.

Sincerely,

A handwritten signature in black ink, appearing to read "Russell J. Kendzior", written over a horizontal line.

Russell J. Kendzior  
President