Chemical Compatibility Guide for: Sili-Thane™ 803 Sealant

NOTICE:

The guide on the following page(s) was provided by the supplier. New Pig Corporation assumes no responsibility, obligation, or liability in conjunction with the use or misuse of the information.

For additional assistance, please contact New Pig Technical Services at 1-800-HOT-HOGS® (468-4647).

100% Money-Back Guarantee

If you're not happy with a product, for any reason, we'll refund every penny of your purchase price. That means we'll refund all sales taxes, shipping costs, and any other incidentals - without tacking on a restocking fee or any other surprise charges. You get ALL your money back. Period.

One Pork Avenue, Tipton, PA 16684-0304 • 1-800-HOT HOGS® (468-4647) • Fax: 1-800-621-PIGS (7447) Email: hothogs@newpig.com • Web: newpig.com

© New Pig Corporation. All rights reserved.



Chemical Resistance of Cured Urethane Sealants

Solvents

Cured urethane sealants are resistant to occasional splash and spillage contact with typical solvents, and they can tolerate room-temperature immersion in ethyl alcohol and water-glycol mixtures. However, long-term immersion to most typical solvents such as those listed below will cause softening and swelling.

- Acetone
- Benzene
- Diesel fuel and gasoline
- Ester solvents
- Methyl alcohol
- Methylethyl ketone (MEK)
- Methylene chloride
- Mineral spirits; lacquer and paint thinner
- Toluene and xylene.

Alkaline (caustic) materials

Cured urethane sealants can tolerate splash and spillage contact with strongly alkaline (caustic) materials but are severely degraded by long-term immersion and by contact with hot caustics. Concentrations as dilute as 10% can cause serious deterioration. Caustic concentrations below 10% can still cause degradation but only upon longer contact. Typical caustics are:

- Caustic soda
- Caustic potash
- Sodium, potassium, calcium and ammonium hydroxides
- Trisodium phosphate solution
- Sodium carbonate solution.

Acids

Cured urethane sealants are resistant to both organic acids and strong inorganic acids in dilute to medium concentrations (25 to 50%) for both occasional and longer term contact; however, acids will cause urethane breakdown if hot or

concentrated.

Typical organic acids:

Typical inorganic acids:

- Hydrochloric (muriatic)
 - Hydrobromic
 - Phosphoric
 - Sulfuric.
- LacticOxalic.

Acetic

Citric

Butyric

Miscellaneous

Cured urethane sealants can tolerate long-term total contact with dilute chlorine (5 ppm) but are degraded by chlorine levels of 100 ppm or above. Sealants will <u>not</u> withstand either total immersion or hot contact with oxidizing materials, such as:

- Chromic acid (>5%)
- Liquid oxygen
- Nitric acid (>75%)
- Perchloric acid (>75%).

Most other materials, such as lubricating oil, sodium chloride and salt solutions, have little effect.

Additional information

Polymeric Systems, Inc., is a part of Whitford Worldwide. For more information, please contact Polymeric Systems or Whitford Plastics Ltd. at:

Polymeric Systems, Inc.

47 Park Avenue

Elverson, PA, USA 19520

800-CAULK IT (800-228-5548)

Tel: [1] 610-286-2500

Email: sales@polymericsystems.com Website: polymericsystems.com

In the EU contact:

Whitford Plastics Ltd.

10, Christleton Court, Manor Park Runcorn, Cheshire, UK WA7 1ST

Tel: [44] (1928) 571000

Email: salesuk@whitfordww.com

Website: whitfordww.com

NON-WARRANTY: ALL RECOMMENDATIONS, STATEMENTS AND TECHNICAL DATA CONTAINED HEREIN ARE BASED ON TESTS WE BELIEVE TO BE RELIABLE AND CORRECT, BUT ACCURACY AND COMPLETENESS OF SAID TESTS ARE NOT GUARANTEED AND ARE NOT TO BE CONSTRUED AS A WARRANTY, EITHER EXPRESS OR IMPLIED. USER SHALL RELY ON HIS OWN INFORMATION AND TESTS TO DETERMINE SUITABILITY OF THE PRODUCT FOR THE INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY RESULTING FROM THIS USE OF THE PRODUCT. MANUFACTURER'S SOLE RESPONSIBILITY SHALL BE TO REPLACE THAT PORTION OF THE PRODUCT OF THE MANUFACTURER THAT PROVES TO BE DEFECTIVE. MANUFACTURER SHALL NOT BE LIABLE TO THE BUYER OR ANY THIRD PARTY FOR INJURY, LOSS OR DAMAGE DIRECTLY OR INDIRECTLY RESULTING FROM USE OF, OR INABILITY TO USE, THE PRODUCT. RECOMMENDATIONS OR STATEMENTS OTHER THAN THOSE CONTAINED IN A WRITTEN AGREEMENT SIGNED BY AN OFFICER OF THE MANUFACTURER SHALL NOT BE BINDING UPON THE MANUFACTURER. 3010-0707 © Polymeric Systems, Inc. 2007